



HYSOL EA 9396

DESCRIPTION

Hysol® EA 9396 is a low viscosity, room temperature curing adhesive system with excellent strength properties at temperatures from -67°F/-55°C to 350°F/177°C. Hysol EA 9396 has a shelf life of one year when stored at 77°F/25°C for separate components. Qualified to MMM-A-132, Rev A, Type 1, Class 3.

Features

Low Viscosity
Room Temperature Cure
Room Temperature Storage
High Strength at Low and High Temperatures

UNCURED PROPERTIES

	<u>Part A</u>	<u>Part B</u>	<u>Mixed</u>
Color	Aqua-Blue	Amber	Green
Viscosity @ 77°F	400 - 1,400 Poise	.7 - 1.1 Poise	35 Poise
Brookfield, HBT	Spdl 4 @ 10 rpm	Spdl 1 @ 100 rpm	Spdl 1 @ 20 rpm
Viscosity @ 25°C	80 Pa•s	0.1 Pa•s	3.5 Pa•s
Brookfield, HBT	Spdl 4 @ 2.1 rad/s	Spdl 1 @ 10.5 rad/s	Spdl 1 @ 2.1 rad/s
Density (g/ml)	1.19	1.00	1.14
Shelf life			
@ <40°F/4°C	1 year	1 year	
@ <77°F/25°C	1 year	1 year	

This material will normally be shipped at ambient conditions, which will not alter our standard warranty, provided that the material is placed into its intended storage upon receipt. Premium shipment is available upon request.

HANDLING

Mixing - This product requires mixing two components together just prior to application to the parts to be bonded. Complete mixing is necessary. The temperature of the separate components prior to mixing is not critical, but should be close to room temperature (77°F/25°C).

Mix Ratio	Part A	Part B
By Weight	100	30

Note: Volume measurement is not recommended for structural applications unless special precautions are taken to assure proper ratios.

Pot Life (450 g mass) 75 - 90 minutes
Method - ASTM D2471 in water bath.

APPLICATION

Mixing

Combine Part A and Part B in the correct ratio and mix thoroughly. THIS IS IMPORTANT! Heat buildup during or after mixing is normal. Do not mix quantities greater than 250 grams as dangerous heat buildup can occur causing uncontrolled decomposition of the mixed adhesive. TOXIC FUMES CAN OCCUR, RESULTING IN PERSONAL INJURY. Mixing smaller quantities will minimize the heat buildup.

Applying

Bonding surfaces should be clean, dry and properly prepared. For optimum surface preparation consult the Hysol Surface Preparation Guide. The bonded parts should be held in contact until the adhesive is set. Handling strength for this adhesive will occur in 24 hours at 77°F/25°C, after which the support

tooling or pressure used during cure may be removed. Since full bond strength has not yet been attained, load application should be small at this time.

Curing

This adhesive may be cured for 3 - 5 days at 77°F/25°C to achieve normal performance. Accelerated cures of 1 hour at 150°F/65°C may be used.

Cleanup

It is important to remove excess adhesive from the work area and application equipment before it hardens. Denatured alcohol and many common industrial solvents are suitable for removing uncured adhesive. Consult with your supplier's information pertaining to the safe and proper use of solvents.

BOND STRENGTH

Tensile - Lap Shear Tensile lap shear strength tested per ASTM D1002 after curing as shown below.

Adherends are 2024-T3 bare aluminum treated with phosphoric acid anodized per ASTM D3933.

Test Temperature °F/°C	Cure 5 days @ 77°F/25°C		Typical Results Cure 1 hour @ 150°F/56°C		Cure 30 min. @ 180°F/80°C	
	psi	MPa	psi	MPa	psi	MPa
-67/-55	3,300	22.8	3,300	22.8	3,500	24.1
77/25	3,500	24.1	4,000	27.6	4,000	27.6
180/82	3,200	22.1	3,300	22.8	3,300	22.8
300/149	1,800	12.4	1,800	12.4	1,900	13.1
350/177	1,250	8.6	1,200	8.3	1,200	8.3

Peel Strength: Bell peel strength tested per ASTM D1367 after curing for 5 days @ 77°F/25°C.

Adherends are 2024-T3 bare aluminum treated with phosphoric acid anodized per ASTM D3933.

Test Temperature °F/°C	Typical Results	
	lbf/in	N/mm
77/25	25	4.4
180/80	20	3.5

Specifications

The above values are typical results under ideal conditions. To establish certification values, please refer to the Dexter Aerospace Specification which defines quality control test values, methods and procedures. For a copy of the Dexter Aerospace Specification, contact Dexter's Literature Desk at (510)458-8000.

Service Temperature: Service temperature is defined as that temperature at which this adhesive still retains 1000 psi/6.9 MPa using test method ASTM D1002 and is approximately 350°F/177°C.

BULK RESIN PROPERTIES

Electrical - tested per ASTM D149, D150.

	<u>0.1 KHz</u>	<u>1.0 KHz</u>	<u>10.0 KHz</u>
Dielectric Constant	4.17	4.12	3.97
Dissipation Factor	0.006	0.017	0.031

HANDLING PRECAUTIONS

Do not handle or use until the Material Safety Data Sheet has been read and understood.

For industrial use only.

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty

containers retain product residue and vapors so obey all precautions when handling empty containers.

PART A

CAUTION! This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

PART B

WARNING! This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Hysol® is a registered trademark of The Dexter Corporation.

Properties listed are typical values and are not intended for use in preparing specifications. Actual values may vary. Recommendations and suggestions contained herein are limited to reasonable commercial use. No express warranties are intended by any representation and there are no warranties which extend beyond the description on the face hereof. The user is advised to use cure conditions when evaluating this product that are as representative as possible of those used in the actual manufactured item.



HYSOL AEROSPACE PRODUCTS
2850 Willow Pass Road
P.O. Box 312
Pittsburg, CA 94565-0031
Tel: (510) 458-8000
Fax: (510) 458-8030

Rev Date
07/01/94