



# SPECIFICATION SHEET

Hempel (Singapore) Pte. Ltd.

SF 10-01 HQ 55

Project: B261 (SSAU-3600-GOM-C42)

Area: EXTERNAL MAIN DECK, EXTERNAL WALKWAYS, UPPER DECK, ACCOMMODATION LEVEL 1/2 DECKS

Area size:

7500 m<sup>2</sup>

Product information:		Shade no.	Volume solids %	Curing agent	Mixing ratio volume	Pot life 20°C	Dry to touch 20°C	Flash point °C	Thinner	Application restrictions Min. temp. °C, Max. RH%
HEMPADUR ZINC 17360		19830	65	97040	4 : 1	2 h	1 h	24	08450	-10
HEMPADUR MASTIC 45881		12170	77	95881	3 : 1	3 h	6 h	35	08450	15
HEMPATHANE TOPCOAT 55210		11480	51	95370	7 : 1	4 h	8 h	33	08080	-10

Data, specifications, directions and recommendations given in this painting specification represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of the intended use is not guaranteed and must be determined by User, Manufacturer and Seller assume no liability in excess of what is stated in our GENERAL CONDITIONS OF SALE, DELIVERY AND SERVICE for results obtained, injury, direct or consequential damage incurred from the use as recommended above, overcoat, or otherwise.

Hempel's Presale System 2.2  
Printed at: 31/03/2004 11:49:13 AM  
Created/Last modified: 31-03-2004 11:48

User name: Ong Kim Choon  
Department name: Protective & Export  
SGOKC0454 Page: 6

Quality Code:  
Environment: Severe

# HEMPEL

Singapore