


SPHERICAL STEEL GRIT



S 930 – S 780 – S 660 – S 550 – S 460 – S 390 – S 330 – S 280 – S 230 – S 170 – S 110 – S 70

Durezza= 40/51 HRC hardness

Peso específico= Min. 7,2 g/cm³ Specific weight

Microstruttura= martensite e bainite rinvenute completamente fine ed omogenea

Composizione Chimica: Chemical composition

C	0,8 %	1,2 %
Si	Min.	0,4 %
Mn	0,35 %	1,2 %
S+P	0,05 %	max

STEEL GRIT USED
1/3rd EACH
S230—S280—S390

**GRANULOMETRIA GRANIGLIA d'ACCIAIO SFERICA
UTILIZZATA IN PARTI UGUALI
S230—S280—S390**

Misure:

[illegible]