

9. Major International Standards

Thickness (mm)	Iron Loss W/kg W15/50	India CSCI ES	India IS 648	Japan JIS C2552 (2000)	IEC IEC 60404-8- 4 (1998)	BS/EU BS EN 10106 (2007)	China GB/T 2521 (1996)	America ASTM A677- 05 (W15/50)
0.35	2.10	—	—	35A210	—	—	—	—
	2.30	—	—	35A230	M230-35A5	—	35W230	—
	2.35	—	—	—	M235-35A5	M235-35A	—	—
	2.50	—	—	35A250	M250-35A5	M250-35A	35W250	36F145(2.52)
	2.70	—	—	35A270	M270-35A5	M270-35A	35W270	36F155(2.70)
	2.87	—	—	—	—	—	—	36F165(2.87)
	3.00	—	—	35A300	M300-35A5	M300-35A	35W300	36F175(3.05)
	3.22	—	—	—	—	—	—	36F185(3.22)
	3.30	—	—	—	M330-35A5	M330-35A	35W330	—
	3.40	—	—	—	—	—	—	36F195(3.40)
	3.60	—	35C360	35A360	M360-35A5	—	35W360	36F205(3.57)
0.50	4.00	—	—	—	—	—	35W400	—
	4.40	35CS440	—	35A440	—	—	35W440	—
	2.30	—	—	50A230	—	—	50W230	—
	2.50	—	—	50A250	M250-50A5	M250-50A	50W250	—
	2.70	—	—	50A270	M270-50A5	M270-50A	50W270	—
	2.90	—	—	50A290	M290-50A5	M290-50A	50W290	47F165(2.87)
	3.10	—	—	50A310	M310-50A5	M310-50A	50W310	47F180(3.13)
	3.30	—	—	—	M330-50A5	M330-50A	50W330	47F190(3.31)
	3.50	—	—	50A350	M350-50A5	M350-50A	50W350	47F200(3.48)
	3.64	—	—	—	—	—	—	47F210(3.64)
	4.00	50CS400	50C400	50A400	M400-50A5	M400-50A	50W400	47F240(4.18)
	4.70	50CS470	50C470	50A470	M470-50A5	M470-50A	50W470	47F280(4.87)
	5.30	—	50C530	—	M530-50A5	M530-50A	—	—
	5.40	—	—	—	—	—	50W540	—
	6.00	50CS600	50C600	50A600	M600-50A5	M600-50A	50W600	—
	7.00	50CS700	50C700	50A700	M700-50A5	M700-50A	50W700	47F400(6.96)
	8.00	50CS800	50C800	50A800	M800-50A5	M800-50A	50W800	47F450(7.84)
	9.40	—	—	—	M940-50A5	M940-50A	—	—
	10.00	50CS1000	50C1000	50A1000	M1000-50A5	—	50W1000	—
	13.00	50CS1300	—	50A1300	—	—	50W1300	—
0.65	3.10	—	—	—	M310-65A5	M310-65A	—	—
	3.30	—	—	—	M330-65A5	M330-65A	—	—
	3.50	—	—	—	M350-65A5	M350-65A	—	64F200(3.48)
	3.66	—	—	—	—	—	—	64F210(3.66)
	3.92	—	—	—	—	—	—	64F225(3.92)
	4.00	—	—	—	M400-65A5	M400-65A	—	64F235(4.09)
	4.33	—	—	—	—	—	—	64F250(4.33)
	4.70	65CS470	65C470	—	M470-65A5	M470-65A	—	64F275(4.79)
	5.30	—	—	—	M530-65A5	M530-65A	—	64F320(5.57)
	6.00	65CS600	65C600	—	M600-65A5	M600-65A	65W600	—
	7.00	65CS700	65C700	—	M700-65A5	M700-65A	65W700	—
	8.00	65CS800	65C800	65A800	M800-65A5	M800-65A	65W800	64F500(8.70)
	10.00	65CS1000	65C1000	65A1000	M1000-65A5	M1000-65A	65W1000	64F550(9.58)
	13.00	65CS1300	—	65A1300	—	—	65W1300	—
	16.00	—	—	65A1600	—	—	65W1600	—