



Cast-Crete, USA LLC.

Tampa

813-621-4641

<http://www.castcrete.com>

If you have questions about specific products or services we provide, please don't hesitate to contact us.



TEK 07-01D

FIRE RESISTANCE RATINGS OF CONCRETE MASONRY ASSEMBLIES

INTRODUCTION

Concrete masonry is widely specified for fire walls and fire barriers because concrete masonry is noncombustible, provides durable fire resistance, and is economical to construct.

Chapter 7 of the International Building Code (IBC) (refs. 2, 3) governs materials and assemblies used for structural fire resistance and fire-rated separation of adjacent spaces. This TEK is based on the provisions of *Code Requirements for Determining Fire Resistance of Concrete and Masonry Construction Assemblies*, ACI/TMS 216.1 (ref. 1), which outlines a procedure to calculate the fire resistance ratings of concrete masonry assemblies. The 2014 edition of the ACI/TMS 216.1 is referenced by the 2015 and 2018 IBC for concrete and masonry materials.

This TEK is based on both prescriptive details and tables as well as the calculated fire resistance procedure, which is practical, versatile and economical. The calculation procedure allows the designer virtually unlimited flexibility to incorporate the excellent fire-resistive properties of concrete masonry into a design. Included are methods for determining the fire resistance rating of concrete masonry walls, columns, lintels, beams, and concrete masonry fire protection for steel columns. Also included are assemblies composed of concrete masonry and other components, including plaster and gypsum wallboard finishes, and multi-wythe masonry components including clay or shale masonry units.

In addition to this TEK, a companion spreadsheet is available that allows users to quickly determine the fire rating of concrete masonry assemblies with various finishes, See **Fire Rating Companion Spreadsheet**, TEK 7-1D (ref. 16).

METHODS OF DETERMINING FIRE RESISTANCE RATINGS

Because full-scale fire testing of representative test specimens is not practical in daily practice due to time and financial constraints, the IBC outlines multiple options for alternatives for fire rating determination:

- standardized calculation procedures, such as those in ACI/TMS 216.1 and in Section 722 of the IBC;
- prescriptive designs such as those in Section 721 of the IBC;
- engineering analysis based on a comparison with tested assemblies;
- third party listing services, such as Underwriters Laboratory; and
- alternative means approved by the building official per Section 104.11 of the IBC.

Of these, the calculation method is an economical and commonly used method of determining concrete masonry fire resistance ratings. The calculations are based on extensive research, which established relationships between the physical properties of materials and the fire resistance rating. The calculation method is fully described in ACI/TMS 216.1 and IBC Section 722, and determines fire resistance ratings based on the equivalent thickness of concrete masonry units and the aggregate types used to manufacture the units.

Private commercial listing services allow the designer to select a fire rated assembly that has been previously tested, classified and listed in a published directory of fire rated assemblies. The listing service also monitors materials and production to verify that the concrete masonry units are and remain in compliance with appropriate standards, which usually necessitates a premium for units of this type. The system also is somewhat inflexible in that little variation from the original tested wall assembly is allowed, including unit size, shape, mix design, constituent materials, and even the plant of manufacture. More information on listing services for fire ratings is provided in **NCMA FAQ 21-14, *What is the difference between fire resistance ratings for masonry assemblies obtained through IBC versus a listing service such as UL or FM?*** (ref. 18).

For prescriptive designs, the IBC provides a series of tables that describes requirements of various assemblies to meet the fire resistance ratings specified. The last two options listed above require justification to the building official that the proposed design is at least the equivalent of what is prescribed in the code.

CALCULATED FIRE RESISTANCE RATINGS

Background

The calculated fire resistance method is based on extensive research and testing of concrete masonry walls. Fire testing of wall assemblies is conducted in accordance with the Standard Test Methods for Fire Tests of Building Construction and Materials, ASTM E119 (ref. 4), which measures four performance criteria, as follows:

- resistance to the transmission of heat through the wall assembly;
- resistance to the passage of hot gases through the wall, sufficient to ignite cotton waste;
- load-carrying capacity of loadbearing walls; and
- resistance to the impact, erosion and cooling effects of a hose stream on the assembly after exposure to the standard fire.

The fire resistance rating of concrete masonry is typically governed by the heat transmission criteria. From the standpoint of life safety (particularly for fire fighters) and reuse, this failure mode is certainly preferable to a structural collapse endpoint, characteristic of many other building materials.

The calculated fire resistance rating information presented here is based on the IBC and ACI/TMS 216.1 (refs. 1, 2, 3).

Equivalent Thickness

Extensive testing has established a relationship between fire resistance and the equivalent solid thickness of concrete masonry walls, as shown in Table 1. Equivalent thickness is essentially the solid thickness that would be obtained if the volume of concrete contained in a hollow unit were recast without core holes (see Figure 1). The equivalent thickness is determined in accordance with *Standard Methods of Sampling and Testing Concrete Masonry Units*, ASTM C140/C140M (ref. 5), and is reported on the C140 test report. If the equivalent thickness is unknown, but the percent solid of the unit is, the equivalent thickness of a hollow unit can be determined by multiplying the percent solid by the unit's actual thickness.

The equivalent thickness of a 100% solid unit or a solid grouted unit is equal to the actual thickness. For partially grouted walls where the unfilled cells are left empty, the equivalent thickness for fire resistance rating purposes is equal to that of an ungrouted unit. For partially grouted walls with filled cells, see the following section.

Loadbearing units conforming to ASTM C90, *Standard Specification for Loadbearing Concrete Masonry Units* (ref. 6), that are commonly available include 100% solid units, 75% solid units, and hollow units meeting minimum required face shell and web dimensions. Typical equivalent thickness values for these units are listed in Table 2.




Figure 1—Equivalent Thickness

Table 1—Fire Resistance Rating Period of Concrete Masonry Assemblies (refs. 1, 2, 3)

Aggregate type in the concrete masonry unit ^c	Minimum required equivalent thickness, in. (mm), for fire resistance rating, hours ^{A, B}														
	4	3 3/4	3 1/2	3 1/4	3	2 3/4	2 1/2	2 1/4	2	1 3/4	1 1/2	1 1/4	1	3/4	1/2
Calcareous or siliceous gravel	6.2	6.0	5.8	5.5	5.3	5.0	4.8	4.5	4.2	3.9	3.6	3.2	2.8	2.4	2.0
Limestone, cinders or unexpanded slag	5.9	5.7	5.5	5.2	5.0	4.8	4.5	4.3	4.0	3.7	3.4	3.1	2.7	2.3	1.9
Expanded clay, shale, or slate	5.1	4.9	4.8	4.6	4.4	4.2	4.0	3.8	3.6	3.4	3.3	2.9	2.6	2.2	1.8
Expanded slag or pumice	4.7	4.5	4.4	4.2	4.0	3.8	3.6	3.4	3.2	3.0	2.7	2.5	2.1	1.9	1.5

^A Fire resistance rating between the hourly fire resistance rating periods listed may be determined by linear interpolation based on the equivalent thickness value of the concrete masonry unit. The requirements of ASTM C55, ASTM C73, ASTM C90 or ASTM C744 (refs. 13, 14, 6, 15) shall apply. Include equivalent thickness of finishes where applicable: see section "Effects of Finishes on Fire Resistance Ratings."

^B Where combustible members are framed into the wall, the thickness of solid material between the end of each member and opposite wall face, or between members set in from opposite sides, must be at least 93% of thickness shown.

^C Minimum required equivalent thickness corresponding to the hourly fire resistance rating for units made with a combination of aggregates shall be determined by linear interpolation based on the percent by volume of each aggregate used in the manufacture.

Table 1—Fire Resistance Rating Period of Concrete Masonry Assemblies (refs. 1, 2, 3)

Table 2—Equivalent Thicknesses of Concrete Masonry Units, in. (mm)

Nominal width, in. (mm)	Based on typical hollow units ^A		Based on percent solid (75%) (100%)	
4 (102)	2.7 (69)	[73.8]	2.7 (69)	3.6 (91)
6 (152)	3.1 (79)	[55.0]	4.2 (107)	5.6 (142)
8 (203)	4.0 (102)	[53.0]	5.7 (145)	7.6 (193)
10 (254)	4.5 (113)	[46.3]	7.2 (183)	9.6 (244)
12 (305)	5.1 (129)	[44.0]	8.7 (221)	11.6 (295)
14 (356)	5.5 (139)	[40.2]	10.2 (259)	13.6 (345)
16 (406)	6.0 (152)	[38.4]	11.7 (297)	15.6 (396)
^A Values in brackets [] are percent solid values based on typical two-core concrete masonry units.				

Table 2—Equivalent Thicknesses of Concrete Masonry Units, in. (mm)

Filling Cells with Loose Fill Material

If all cells of hollow unit masonry are filled with an approved material, the equivalent thickness of the assembly is the actual thickness. This also applies to partially grouted concrete masonry walls where all ungrouted cells are filled with an approved material.

Applicable fill materials are: grout, sand, pea gravel, crushed stone, or slag that comply with ASTM C33/C33M, *Standard Specification for Concrete Aggregates* (ref. 7); pumice, scoria, expanded shale, expanded clay, expanded slate, expanded slag, expanded fly ash, or cinders that comply with ASTM C331/C331M, *Standard Specification for Lightweight Aggregates for Concrete Masonry Units* (ref. 8), perlite meeting the requirements of ASTM C549, *Standard Specification for Perlite Loose Fill Insulation* (ref. 9), or vermiculite complying with C516, *Standard Specification for Vermiculite Loose Fill Thermal Insulation* (ref. 10).

Wall Assembly Fire Ratings

The fire resistance rating is determined in accordance with Table 1 utilizing the appropriate aggregate type used in the masonry unit and the equivalent thickness.

Units manufactured with a combination of aggregate types are addressed by footnote C, which may be expressed by the following equation (see also the blended aggregate example, below):

$$T_r = (T_1 \times V_1) + (T_2 \times V_2) + \dots + (T_n \times V_n)$$

where:

- T_r = required equivalent thickness for a specific fire resistance rating of an assembly constructed of units with combined aggregates, in. (mm)
- $T_1, T_2, \dots T_n$ = required equivalent thickness from Table 1 for a specific fire resistance rating of a wall constructed of units with aggregate types 1, 2, ... n , respectively, in. (mm)
- $V_1, V_2, \dots V_n$ = fractional volume of aggregate types 1, 2, ... n , respectively, used in the manufacture of the unit (note that the clarification of “dry-rodded volume” was added to the 2007 edition of ACI/TMS 216.1, although this verbiage is not included in the IBC.)

Blended aggregate example:

The required equivalent thickness of an assembly constructed of units made with expanded shale (80% by volume), and calcareous sand (20% by volume), to meet a 3-hour fire resistance rating is determined as follows. From Table 1:

$$T_1 \text{ for expanded shale (3 hr rating)} = 4.4 \text{ in. (112 mm)}$$

$$T_2 \text{ for calcareous sand (3 hr rating)} = 5.3 \text{ in. (135 mm)}$$

$$T_r = (T_1 \times V_1) + (T_2 \times V_2)$$

$$T_r = (4.4 \times 0.80) + (5.3 \times 0.20) = 4.6 \text{ in. (116 mm)}$$

Multi-Wythe Wall Assemblies

The fire resistance rating of multi-wythe walls (Figure 2) is based on the fire resistance of each wythe and the air space between each wythe using the following equation:

$$R = (R_1^{0.59} + R_2^{0.59} + \dots + R_n^{0.59} + A_1 + A_2 + \dots A_n)^{1.7}$$

Where:

- $R_1, R_2, \dots R_n$ = fire resistance rating of wythe 1, 2, ... n , respectively (hr).
- $A_1, A_2, \dots A_n$ = 0.30, factor for each air space, 1, 2,... n , respectively, having a width of ½ in. (13 mm) or more between wythes. Note that it does not matter which side is exposed to the fire.

For multi-wythe walls of clay and concrete masonry, use the values in Table 3 for the brick wythe in the above equation.




Figure 2—Variables for Determining the Fire Resistance Rating of a Multi-Wythe Masonry Wall

Table 3—Fire Resistance of Brick or Tile of Clay or Shale (refs. 1, 2, 3)

Material type	Minimum equivalent thickness ^A for fire resistance rating, in. (mm)			
	4 hours	3 hours	2 hours	1 hours
≥ 75% solid	6.0 (152)	4.9 (124)	3.8 (97)	2.7 (69)
Hollow units ^B	5.0 (127)	4.3 (109)	3.4 (86)	2.3 (58)
Hollow units ^C	6.6 (168)	5.5 (140)	4.4 (112)	3.0 (76)
^A See <i>Equivalent Thickness</i> section for calculation. ^B Unfilled hollow units. ^C Grouted or filled according to the <i>Filling Cells with Loose Fill Material</i> section.				

Table 3—Fire Resistance of Brick or Tile of Clay or Shale (refs. 1, 2, 3)

Reinforced Concrete Masonry Columns

Concrete masonry column fire testing evaluates the ability of the column to carry design loads under standard fire test conditions. Based on a compendium of fire tests, the fire resistance rating of reinforced concrete masonry columns is based on the least plan dimension of the column as indicated in Table 4. The minimum required cover over the vertical reinforcement is 2 in. (51 mm).

Table 4—Reinforced Concrete Masonry Columns
(refs. 1, 2, 3)

Minimum column dimensions, in. (mm), for fire resistance rating of:			
1 hour	2 hours	3 hours	4 hours
8 (203)	10 (254)	12 (305)	14 (356)

📷 Table 4—Reinforced Concrete Masonry Columns (refs. 1, 2, 3)

Concrete Masonry Lintels

Fire testing of concrete masonry beams and lintels evaluates the ability of the member to sustain design loads under standard fire test conditions. This is accomplished by ensuring that the temperature of the tensile reinforcement does not exceed 1,100 °F (593 °C) during the rating period.

The calculated fire resistance rating of concrete masonry lintels is based on the nominal thickness of the lintel and the minimum cover of longitudinal reinforcement (see Table 5). The cover requirements protect the reinforcement from strength degradation due to excessive temperature during the fire exposure period. Cover requirements may be provided by masonry units, grout, or mortar. Note that for 3 and 4 hour requirements, not enough cover is available for 6-in. (152 mm) masonry; however, if a special analysis indicates that the reinforcement is not necessary or not needed, such as when conditions for arching action are present, the cover requirements may be waived. See **TEK 17-01D** (ref. 12) for lintel design and conditions for arching action.

**Table 5—Reinforced Concrete Masonry Lintels
Minimum Longitudinal Reinforcing Cover,
in. (mm) (refs. 1, 2, 3)**

Nominal lintel width, in. (mm)	Fire resistance rating			
	4 hours	3 hours	2 hours	1 hours
6 (152)	1½ (38)	2 (51)	A	A
8 (203)	1½ (38)	1½ (38)	1¾ (38)	3 (76)
10 (254) or more	1½ (38)	1½ (38)	1½ (38)	1¾ (44)
^A May be permitted with a more detailed analysis per ACI 216.1/TMS 216—i.e. conditions for arching action.				

Table 5—Reinforced Concrete Masonry Lintels Minimum Longitudinal Reinforcing Cover, in. (mm) (refs. 1, 2, 3)

Control Joints

Figure 3 shows control joint details in fire-rated wall assemblies in which openings are not permitted or where openings are required to be protected. Maximum joint width is ½ in. (13 mm). Although these details are not directly in the IBC, they are included by reference in ACI/TMS 216.1.

In addition to these prescriptive fire resistance rated control joints, other control joints may be permitted in fire rated masonry walls. For example, the IBC and ACI/TMS 216.1 include provisions for ceramic fiber joint protection for precast panels, which are similar to concrete masonry walls in that both rely on concrete for fire protection, and both are governed by the ASTM E119 heat transmission criteria (see Figure 4). The first two categories of aggregate types in Table 1 would correspond to the carbonate or siliceous aggregate concrete curve and the last two aggregate categories of Table 1 would correspond to the semi-lightweight or lightweight concrete curve. For example, for an 8-in. (203-mm) limestone aggregate concrete masonry wall with a maximum control joint width of ½ in. (13 mm), a 1 in. (25 mm) thickness (measured perpendicular to the face of the wall) of ceramic fiber in the joint can be used in walls with fire resistance ratings up to 3 hours, while a 2 in. (51 mm) thickness can be used in the joints of a 4-hour wall.




Figure 3—Control Joints for Fire Resistant Concrete Masonry Assemblies (ref. 1)




Figure 4—Ceramic Fiber Joint Protection

Steel Columns Protected by Concrete Masonry

Fire testing of a steel column protected by concrete masonry evaluates the structural integrity of the steel column under fire test conditions, by measuring the temperature rise of the steel. The calculated fire resistance rating of steel columns protected by concrete masonry, as illustrated in Figure 5, is determined by:

$$R = 0.401(A_{st}/p_s)^{0.7} + [0.285(T_{ea}^{1.6}/k_{cm}^{0.2})] \times [1.0 + 42.7\{(A_{st}/w_{cm}T_{ea})/(0.25p + T_{ea})\}^{0.8}] \text{ (English Units)}$$

$$R = 1.019(A_{st}/p_s)^{0.7} + [1.413(T_{ea}^{1.6}/k_{cm}^{0.2})] \times [1.0 + 1736.41\{(A_{st}/w_{cm}T_{ea})/(6.35p + 2.54T_{ea})\}^{0.8}] \text{ (Metric Units)}$$

where:

- A_{st} = cross-sectional area of the steel column, in.², (mm²)
- p_s = heated perimeter of steel column, in. (mm)
- T_{ea} = equivalent thickness of concrete masonry assembly, in. (mm)
- k_{cm} = thermal conductivity of concrete masonry at room temperature, Btu/(hr·ft²·°F), (kcal/(m·hr·°C))
- w_{cm} = density of masonry protection, lb/ft³ (kg/m³)
- p = inner perimeter of masonry protection, in. (mm)

For more information on steel columns protected by concrete masonry, see TEK **7-6A**, Steel Column Fire Protection (ref. 11).




Figure 5—Details of Concrete Masonry Column Protection for Commonly Used Shapes

**Table 6—Concrete Masonry
Conductivity (refs. 1, 2, 3)**

Density, d_m pcf (kg/m ³)	Thermal conductivity ^A , K Btu/hr ft °F (W/m·C)
80 (1,281)	0.207 (0.358)
85 (1,362)	0.228 (0.394)
90 (1,442)	0.252 (0.436)
95 (1,522)	0.278 (0.481)
100 (1,602)	0.308 (0.533)
105 (1,682)	0.340 (0.588)
110 (1,762)	0.376 (0.650)
115 (1,842)	0.416 (0.720)
120 (1,922)	0.459 (0.749)
125 (2,002)	0.508 (0.879)
130 (2,082)	0.561 (0.971)
135 (2,162)	0.620 (1.073)
140 (2,243)	0.685 (1.186)
145 (2,323)	0.758 (1.312)
150 (2,403)	0.837 (1.449)
^A Thermal conductivity at 70 °F. °C = (°F-32)(5/9)	

Table 6—Concrete Masonry Conductivity (refs. 1, 2, 3)

Effects of Finish Materials on Fire Resistance Ratings

In many cases, drywall, plaster or stucco finishes are used on concrete masonry walls. While finishes are normally applied for architectural reasons, they can also provide additional fire resistance. The IBC and ACI/TMS 216.1 make provision for calculating the additional fire resistance provided by these finishes.

Note that when finishes are used to achieve the required fire rating, the masonry alone must provide at least one-half of the total required rating and the contribution of the finish on the non-fire-exposed side can not be more than one-half of the contribution of the masonry alone. This is to assure structural integrity during a fire. The finish material must also be continuous over the entire wall.

Certain finishes deteriorate more rapidly when exposed to fire than when they are on the non-fire side of the wall. Therefore, two separate tables are required. Table 7 applies to finishes on the non-fire-exposed side of the wall, and Table 8 applies to finishes on the fire-exposed side.

For finishes on the non-fire-exposed side of the wall, the finish is converted to an equivalent thickness of concrete masonry by multiplying the finish thickness by the factor given in Table 7. The result, T_{ef} , is then added to the concrete masonry wall equivalent thickness, T_e , and used in Table 1 to determine the wall's fire resistance rating (i.e., the equivalent thickness of concrete masonry assemblies, $T_{ea} = T_e + T_{ef}$).

For finishes on the fire-exposed side of the wall, a time (from Table 8) is assigned to the finish. This time is added to the fire resistance rating determined for the base wall and non-fire-exposed side finish, if any. The times listed in Table 8 are essentially the length of time the various finishes will remain intact when exposed to fire (i.e., on the fire-exposed side of the wall).

When calculating the fire resistance rating of a wall with finishes, two calculations are performed, assuming each side of the wall is the fire-exposed side. The fire rating of the wall assembly is the lower of the two. Typically, for an exterior wall with a fire separation distance greater than 5 ft (1,524 mm), fire needs be considered on the interior side only.

Table 7—Multiplying Factor for Finishes on Non-Fire-Exposed Side of Wall (refs. 1, 2, 3)		
Type of finish applied to wall	Aggregate type in concrete masonry:	
	Siliceous, calcareous, limestone, cinders, air-cooled blasting furnace slag	80% or more by volume of expanded shale, slate, or clay, expanded slag or pumice
Portland cement-sand plaster	1.00	0.75 ^{A,C}
Gypsum-sand plaster	1.25	1.00
Gypsum-vermiculite or perlite plaster	1.75	1.25 ^B
Gypsum wall-board	3.00	2.25
^A For portland cement-sand plaster $\frac{5}{8}$ in. (16 mm) or less in thickness and applied directly to concrete masonry on the non-fire-exposed side, the multiplying factor is 1.0. ^B For expanded shale with less than 20% sand, a multiplying factor of 1.50 may be used per IBC. ^C For 100% expanded slag, expanded clay or pumice, and portland cement-sand plaster not meeting the stipulations of footnote A, the multiplying factor shall be 0.50 per IBC.		

Table 8—Time Assigned to Finish Materials on Fire-Exposed Side of Wall (refs. 1, 2, 3)

Finish description:	Time, min.
Gypsum wallboard	
$\frac{3}{8}$ in. (10 mm)	10
$\frac{1}{2}$ in. (13 mm)	15
$\frac{5}{8}$ in. (16 mm)	20
Two layers of $\frac{3}{8}$ in. (10 mm)	25
One layer $\frac{3}{8}$ in. (10 mm) and one layer $\frac{1}{2}$ in. (13 mm)	35
Two layers of $\frac{1}{2}$ in. (13 mm)	40
Type "X" gypsum wallboard	
$\frac{1}{2}$ in. (13 mm)	25
$\frac{5}{8}$ in. (16 mm)	40
Direct-applied gypsum wallboard plaster ^A	
Portland cement-sand plaster on metal lath	
$\frac{3}{4}$ in. (19 mm)	20
$\frac{7}{8}$ in. (22 mm)	25
1 in. (25 mm)	30
Gypsum-sand plaster on $\frac{3}{8}$ in. (10 mm)	
$\frac{1}{2}$ in. (13 mm)	35
$\frac{5}{8}$ in. (16 mm)	40
$\frac{3}{4}$ in. (19 mm)	50
Gypsum-sand plaster on metal lath	
$\frac{3}{4}$ in. (19 mm)	35
$\frac{7}{8}$ in. (22 mm)	40
1 in. (25 mm)	50
^A For the purposes of determining the contribution of portland cement-sand plaster to the equivalent thickness of concrete masonry for use in Table 1, use either the actual plaster thickness or $\frac{5}{8}$ in. (16 mm), whichever is smaller.	

Installation of Finishes

Finishes that contribute to the total fire resistance rating of a wall must meet certain minimum installation requirements. Plaster and stucco are applied in accordance with the provisions of the building code without further modification.

Gypsum wallboard and gypsum lath are to be attached to wood or metal furring strips spaced a maximum of 16 in. (406 mm) o.c., and must be installed with the long dimension parallel to the furring members. All horizontal and vertical joints must be supported and finished.

UNCONVENTIONAL AGGREGATES

In recent years, manufacturers of concrete masonry products have been exploring the use of alternative materials in the production of concrete masonry units. Some of these materials have not been evaluated using standardized fire resistance test methods or have been evaluated only to a limited degree. Such unconventional materials, which are typically used as a replacement for conventional aggregates, may not be covered within existing codes and standards due to their novelty or proprietary nature.

While test methods such as ASTM E119 define procedures for evaluating the fire resistance properties of concrete masonry assemblies, including those constructed using unconventional constituent materials, there has historically been no defined procedure for applying the results of ASTM E119 testing to standardized calculation procedures available through ACI/TMS 216.1. To provide consistency in applying the results of full-scale ASTM E119 testing to established calculation procedures, NCMA has developed a guideline for this purpose. See NCMA **FAQ -18-14, How is the fire resistance of a concrete masonry assembly calculated when using unconventional aggregates?** (ref. 17).

This guideline stipulates that when applying the fire resistance calculation procedure of ACI/TMS 216.1 to products manufactured using aggregate types that are not listed in ACI/TMS 216.1, at least two full-scale ASTM E119 tests must be conducted on assemblies containing the unconventional material. Based on the results of this testing, an expression can be developed in accordance with this industry practice that permits the fire resistance of units produced with such aggregates to be calculated for interpolated values of equivalent thickness and proportion of non-listed aggregate.

References

1. Code Requirements for Determining Fire Resistance of Concrete and Masonry Construction Assemblies, ACI/TMS 216.1-14. American Concrete Institute and The Masonry Society, 2014.
2. International Building Code 2015. International Code Council, 2015.
3. International Building Code 2018. International Code Council, 2018.

4. Standard Test Methods for Fire Tests of Building Construction and Materials, ASTM E119-18c. ASTM International, Inc., 2018.
5. Standard Methods for Sampling and Testing Concrete Masonry Units, ASTM C140/C140M-18. ASTM International, Inc., 2018.
6. Standard Specification for Loadbearing Concrete Masonry Units, ASTM C90-16a. ASTM International, Inc., 2016.
7. Standard Specification for Concrete Aggregates, ASTM C33/C33M-18. ASTM International, Inc., 2018.
8. Standard Specification for Lightweight Aggregates for Concrete Masonry Units, ASTM C331/C331M-17. ASTM International, Inc., 2017.
9. Standard Specification for Perlite Loose Fill Insulation, ASTM C549-18. ASTM International, Inc., 2018.
10. Standard Specification for Vermiculite Loose Fill Thermal Insulation, ASTM C516-08 (2013). ASTM International, Inc., 2013.
11. Steel Column Fire Protection, [TEK 7-6A](#). National Concrete Masonry Association, 2009.
12. Allowable Stress Design of Concrete Masonry Lintels, [TEK 17-1D](#). National Concrete Masonry Association, 2011.
13. Standard Specification for Concrete Building Brick, ASTM C55-17. ASTM International, Inc., 2017.
14. Standard Specification for Calcium Silicate Brick (Sand-Lime Brick), ASTM C73-17. ASTM International, Inc., 2017.
15. Standard Specification for Prefaced Concrete and Calcium Silicate Masonry Units, ASTM C744-16. ASTM International, Inc., 2016.
16. *Fire Rating Companion Spreadsheet*, [TEK 7-1D](#), National Concrete Masonry Association, 2017.
17. *How is the fire resistance of a concrete masonry assembly calculated when using unconventional aggregates?*, [FAQ 18-14](#), National Concrete Masonry Association, 2014.
18. *What is the difference between fire resistance ratings for masonry assemblies obtained through IBC versus a listing service such as UL or FM?*, [FAQ 21-14](#), National Concrete Masonry Association, 2014.

NCMA TEK 07-01D, Revised 2018.

NCMA and the companies disseminating this technical information disclaim any and all responsibility and liability for the accuracy and the application of the

Keywords

calculated fire resistance rating

columns

control joints

equivalent thickness

fire resistance ratings

fire walls

lintels

multi-wythe walls

specifications

steel column protection