


















STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
 No Grade Mark	SAE J429 Grade 1	Bolts, Screws, Studs	Low- or Medium-Carbon Steel	1/4 THRU 1 ½	33,000	36,000	60,000
			Low-Carbon Steel	1/4 thru 4	--	--	
	SAE J429 Grade 2		Low- or Medium-Carbon Steel	1/4 thru 3/4 Over 3/4 thru 1 ½	55,000 33,000	57,000 36,000	74,000 60,000
 No Grade Mark	SAE J429 Grade 4	Studs	Medium-Carbon Cold-Drawn Steel	1/4 thru 1 ½	--	100,000	115,000
 	ASTM A307 Grades A&B	Bolts, Screws, Studs	Low- or Medium-Carbon Steel	1/4 THRU 1 ½	33,000	36,000	60,000
			Low-Carbon Steel	1/4 thru 4	--	--	
			Low- or Medium-Carbon Steel	1/4 thru 3/4 Over 3/4 thru 1 ½	55,000 33,000	57,000 36,000	74,000 60,000
	ASTM A193 Grade B5	Bolts, Screws, Studs for High-Temperature Service	AISI 501	1/4 thru 4	--	80,000	100,000
	ASTM A193 Grade B6	Bolts, Screws, Studs for High-Temperature Service	AISI 410	1/4 thru 4	--	85,000	110,000
	ASTM A193 Grade B7	Bolts, Screws, Studs for High-Temperature Service	AISI 4140, 4142, or 4145	1/4 thru 2 ½ Over 2 ½ thru 4 Over 4 thru 7	-- -- --	105,000 95,000 75,000	125,000 115,000 100,000
	ASTM A193 Grade B16	Bolts, Screws, Studs for High-Temperature Service	CrMoVa Alloy Steel	1/4 thru 2 ½ Over 2 ½ thru 4 Over 4 thru 7	-- -- --	105,000 95,000 85,000	125,000 115,000 100,000

STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
	ASTM A193 Grade B8	Bolts, Screws, Studs for High-Temperature Service	AISI 304	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8C	Bolts, Screws, Studs for High-Temperature Service	AISI 347	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8M	Bolts, Screws, Studs for High-Temperature Service	AISI 316	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8T	Bolts, Screws, Studs for High-Temperature Service	AISI 321	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8	Bolts, Screws, Studs for High-Temperature Service	AISI 304 Strain-Hardened	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8C	Bolts, Screws, Studs for High-Temperature Service	AISI 347 Strain-Hardened	1/4 and Larger 1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- -- --	30,000 100,000 80,000 65,000 50,000	75,000 125,000 115,000 105,000 100,000
	ASTM A193 Grade B8M	Bolts, Screws, Studs for High-Temperature Service	AISI 316 Strain-Hardened	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- --	95,000 80,000 65,000 50,000	110,000 100,000 95,000 90,000
	ASTM A193 Grade B8T	Bolts, Screws, Studs for High-Temperature Service	AISI 321 Strain-Hardened	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 ¼ Over 1 ¼ thru 1 ½	-- -- -- --	100,000 80,000 65,000 50,000	125,000 115,000 105,000 100,000
	ASTM A320 Grade L7	Bolts, Screws, Studs for Low-Temperature Service	AISI 4140, 4142, or 4145	1/4 thru 2 ½	--	105,000	125,000









STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
	ASTM A320 Grade L7A	Bolts, Screws, Studs for Low-Temperature Service	AISI 4037	1/4 thru 2 1/2	--	105,000	125,000
	ASTM A320 Grade L7B	Bolts, Screws, Studs for Low-Temperature Service	AISI 4137	1/4 thru 2 1/2	--	105,000	125,000
	ASTM A320 Grade L7C	Bolts, Screws, Studs for Low-Temperature Service	AISI 8740	1/4 thru 2 1/2	--	105,000	125,000
	ASTM A320 Grade L43	Bolts, Screws, Studs for Low-Temperature Service	AISI 4340	1/4 thru 4	--	105,000	125,000
	ASTM A320 Grade B8	Bolts, Screws, Studs for Low-Temperature Service	AISI 304	1/4 and Larger	--	30,000	75,000
	ASTM A320 Grade B8C	Bolts, Screws, Studs for Low-Temperature Service	AISI 347	1/4 and Larger	--	30,000	75,000
	ASTM A320 Grade B8T	Bolts, Screws, Studs for Low-Temperature Service	AISI 321	1/4 and Larger	--	30,000	75,000
	ASTM A320 Grade B8F	Bolts, Screws, Studs for Low-Temperature Service	AISI 303 or 303Se	1/4 and Larger	--	30,000	75,000
	ASTM A320 Grade B8M	Bolts, Screws, Studs for Low-Temperature Service	AISI 316	1/4 and Larger	--	30,000	75,000









STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
	ASTM A320 Grade B8	Bolts, Screws, Studs for Low-Temperature Service	AISI 304	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 1/4 Over 1 1/4 thru 1 1/2	-- -- -- --	100,000 80,000 65,000 50,000	100,000 80,000 65,000 50,000
	ASTM A320 Grade B8C	Bolts, Screws, Studs for Low-Temperature Service	AISI 347	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 1/4 Over 1 1/4 thru 1 1/2	-- -- -- --	100,000 80,000 65,000 50,000	100,000 80,000 65,000 50,000
	ASTM A320 Grade B8T	Bolts, Screws, Studs for Low-Temperature Service	AISI 316	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 1/4 Over 1 1/4 thru 1 1/2	-- -- -- --	100,000 80,000 65,000 50,000	100,000 80,000 65,000 50,000
	ASTM A320 Grade B8F	Bolts, Screws, Studs for Low-Temperature Service	AISI 321	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 1/4 Over 1 1/4 thru 1 1/2	-- -- -- --	100,000 80,000 65,000 50,000	100,000 80,000 65,000 50,000
	ASTM A320 Grade B8M	Bolts, Screws, Studs for Low-Temperature Service	AISI 303 or 303Se	1/4 thru 3/4 Over 3/4 thru 1 Over 1 thru 1 1/4 Over 1 1/4 thru 1 1/2	-- -- -- --	100,000 80,000 65,000 50,000	100,000 80,000 65,000 50,000
	SAE J429 Grade 5	Bolts, Screws	Medium-Carbon Steel, Quenched and Tempered	1/4 thru 1 Over 1 thru 1 1/2	85,000 74,000	92,000 81,000	120,000 105,000
	ASTM A449	Bolts, Screws, Studs	Medium-Carbon Steel, Quenched and Tempered	1/4 thru 1 Over 1 thru 1 1/2 Over 1 1/2 thru 3	85,000 74,000 55,000	92,000 81,000 58,000	120,000 105,000 90,000
	SAE J429 Grade 5.1	Sems	Low- or Medium-Carbon Steel, Quenched and Tempered	#6 thru 3/8	85,000	--	120,000
	SAE J429 Grade 5.2	Bolts, Screws	Low-Carbon Martensitic Steel, Quenched and Tempered	1/4 thru 1	85,000	92,000	120,000








STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
	ASTM A325 Type 1	High-Strength Structural Bolts	Medium-Carbon Steel, Quenched and Tempered	1/2 thru 1 1 1/8 thru 1 1/2	85,000 74,000	92,000 81,000	120,000 105,000
	ASTM A325 Type 2	High-Strength Structural Bolts	Low-Carbon Marten- sitic Steel, Quenched and Tempered	1/2 thru 1	85,000	92,000	120,000
	ASTM A325 Type 3	High-Strength Structural Bolts	Atmospheric-Corrosion-Resisting Steel, Quenched and Tempered	1/2 thru 1 1 1/8 thru 1 1/2	85,000 74,000	92,000 81,000	120,000 105,000
	ASTM A354 Grade BB	Bolts, Studs	Alloy Steel, Quenched and Tempered	1/4 thru 2 1/2 2 3/4 thru 4	80,000 75,000	83,000 78,000	105,000 100,000
	ASTM A354 Grade BC	Bolts, Studs	Alloy Steel, Quenched and Tempered	1/4 thru 2 1/2 2 3/4 thru 4	105,000 95,000	109,000 99,000	125,000 115,000
	ASTM J429 Grade 7	Bolts and Screws	Medium-Carbon Alloy Steel, Quenched and Tempered	1/4 thru 1 1/2	105,000	115,000	133,000
	SAE J429 Grade 8	Bolts, Screws	Alloy Steel, Quenched and Tempered	1/4 thru 1 1/2	120,000	130,000	150,000
	ASTM A354 Grade BD						
 <i>No Grade Mark</i>	SAE J429 Grade 8.1	Studs	Medium-Carbon Alloy or SAE 1041 Modified Elevated-Temperature Drawn Steel	1/4 thru 1 1/2	120,000	130,000	150,000

STANDARD BOLT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.










Identification Grade Mark	Specification	Fastener Description	Material	Nominal Size Range (in.)	Mechanical Properties		
					Proof Load (psi)	Yield Strength Min (psi)	Tensile Strength Min (psi)
	ASTM A490	High-Strength Structural Bolts	Alloy Steel, Quenched and Tempered	1/2 thru 1 1/2	120,000	130,000	150,000 min 170,000 max
 No Grade Mark	ISO R898 Class 4.6	Bolts, Screws, Studs	Low- or Medium-Carbon Steel, Quenched and Tempered	All sizes through 1 1/2	33,000	36,000	60,000
 No Grade Mark	ISO R898 Class 5.8	Bolts, Screws, Studs	Low- or Medium-Carbon Steel, Quenched and Tempered	All sizes through 1 1/2	55,000	57,000	74,000
 	ISO R898 Class 8.8	Bolts, Screws, Studs	Medium-Carbon Steel, Quenched and Tempered	All sizes through 1 1/2	85,000	92,000	120,000
 	ISO R898 Class 10.9	Bolts, Screws, Studs	Alloy Steel, Quenched and Tempered	All sizes through 1 1/2	120,000	130,000	150,000

All-Pro Threaded Head Marking








STANDARD NUT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.


Identification Grade Mark	Specification	Material	Nominal Size Range (in.)	Proof Load (psi)	Hardness Rockwell		See Note
					Min	Max	
 No Grade Mark	ASTM A563 Grade A	Carbon Steel	1/4 thru 1 1/2	69	B55	C32	3,4
	ASTM A563 Grade A			69	B55	C32	
	ASTM A563 Grade B		1/4 thru 1 Over 1 thru 1 1/2	120 105	B69	C32	
	ASTM A563 Grade C	Carbon Steel; May be Quenched and Tempered	1/4 thru 4	144	B78	C38	5
	ASTM A563 Grade C3	Atmospheric-Corrosion-Resistant Steel; May be Quenched and Tempered	1/4 thru 4	144	B78	C38	5, 9
	ASTM A563 Grade D	Carbon Steel; May be Quenched and Tempered	1/4 thru 4	150	B84	C38	6
	ASTM A563 Grade DH	Carbon Steel, Quenched and Tempered	1/4 thru 4	175	C24	C38	6
	ASTM A563 Grade DH3	Atmospheric-Corrosion-Resistant Steel, Quenched and Tempered	1/4 thru 4	175	C24	C38	5,9
	ASTM A194 Grade 1	Carbon Steel	1/4 thru 4	130	B70	-----	7
	ASTM A194 Grade 2	Medium-Carbon Steel	1/4 thru 4	150	159	352	7,8
	ASTM A194 Grade 2H	Medium-Carbon Steel, Quenched and Tempered	1/4 thru 4	175	C24	C38	7

STANDARD NUT IDENTIFICATION MARKINGS

This technical information is supplied as a courtesy. All-Pro Threaded neither employs nor maintains an engineering or technical staff, and All-Pro is merely supplying certain manufacturing, technical, and/or design specifications and data received by All-Pro Threaded from the products' manufacturer or taken from consensus standards, and is in no manner originated, developed, created, enhanced, altered, or approved by All-Pro Threaded.

Identification Grade Mark	Specification	Material	Nominal Size Range (in.)	Proof Load (psi)	Hardness Rockwell		See Note
					Min	Max	
	ASTM A194 Grade 2HM	Medium-Carbon Steel, Quenched and Tempered	1/4 thru 4	150	159	237	7,8
	ASTM A194 Grade 4	Medium-Carbon Alloy Steel, Quenched and Tempered	1/4 thru 4	175	C24	C38	7
	ASTM A194 Grade 7	Medium-Carbon Alloy Steel, Quenched and Tempered	1/4 thru 4	175	C24	C38	7
	ASTM A194 Grade 7M	Medium-Carbon Alloy Steel, Quenched and Tempered	1/4 thru 4	150	159	237	7
	ASTM A194 Grade 8	Stainless AISI 304	1/4 thru 4	80	126	300	10
	ASTM A194 Grade 8M	Stainless AISI 316	1/4 thru 4	80	126	300	10

All-Pro Threaded Head Marking



NOTES:

- In addition to the indicated grade marking, all grades, except A563 Grades O, A, and B, must be marked for manufacturer identification.
- The markings shown for all grades of A194 nuts are for cold-formed and hot-formed nuts. When nuts are machined from bar stock the nut must be additionally marked with the letter "B."
- Nuts are not required to be marked unless specified by the purchaser. When marked, the identification marking shall be the grade letter O, A, or B.
- Properties shown are those of non-plated or non-coated coarse-thread hex nuts.
- Properties shown are those of coarse-thread heavy hex nuts.
- Properties shown are those of coarse-thread heavy hex nuts.
- Properties shown are those of coarse 8-thread heavy hex nuts.
- Hardnesses are Brinell Hardness numbers.
- The nut manufacturer, at his option, may add other markings to indicate the use of atmospheric-corrosion-resistant steel.
- Nuts that are carbide-solution-treated require additional letter A-8A or 8MA.
- Specifications:
 - ASTM A563: Carbon and Alloy Steel Nuts
 - ASTM A194/A194M: Carbon and Alloy Steel Nuts for Bolts for High-Pressure and High-Temperature Service

Other, less common, grades exist but are not listed here.