



# Filler Metals

Selection Guide

**LINCOLN**  
**ELECTRIC**



## FILLER METAL SELECTOR GUIDE

This report lists recommended Lincoln Electric matching strength Manual Stick (SMAW), MIG (GMAW), Submerged Arc (SAW), Self-Shielded and Gas-Shielded Flux-Cored (FCAW-S, FCAW-G) for ASTM, API and ABS classified steels. Also included is general information on each classification such as tensile strength, yield strength and steel chemistry.

### TABLE OF CONTENTS

Description	Page No.
Technical Notes, Codes .....	.3
American Society of Testing and Materials (ASTM) Specifications .....	4 - 25
American Petroleum Institute (API) Specifications .....	26-27
American Bureau of Shipping (ABS) Specifications .....	See ASTM A131
Special Consumable Product Services .....	26-27

The serviceability of a product or structure utilizing these suggested consumables is and must be the sole responsibility of the builder/user. Many factors must be taken into consideration when a filler metal is selected for a specific application. These factors include, but are not limited to, the type of steel, type of weld, loading on the welded joint, applicable codes, level of preheat, level of restraint, position of welding, condition of the steel, and service conditions. This guide provides matching strength filler metal options -- see discussion about undermatching below. The primary focus of these suggestions is based upon the yield and tensile strength properties of the weld deposit as compared to the base metal yield and tensile strength properties. These suggested products may not meet all code or application requirements. Suggested filler metals may not always meet Charpy V-Notch (CVN) application requirements --reference comments below on CVN's.

Reference is made to ASTM and API specifications and classifications and the requisite properties specified in those documents. These specifications are subject to change, and the user should consult the latest version of these documents to ensure that these descriptions are up-to-date. These filler metal suggestions "match" the base metal properties; that is, the yield and tensile strength are expected to meet or exceed the minimum specified properties of the steel. Matching filler metal is typically required for complete joint penetration groove welds in tension. However, fillet welds loaded in shear seldom require matching filler metal. Depending on the type of weld joint and loading, lower filler metal strengths may be acceptable or desirable for specific designs. Also, codes, specifications, or contract documents may require specific mechanical properties that these recommendations do not meet. In those cases, electrode selection should be limited to those products that meet the specific application requirements. Suggested electrodes in this Selector Guide include those that have deposit weld metal with different levels of diffusible hydrogen. High levels of hydrogen can cause weld metal and base metal cracking. The permissible level of hydrogen in a weld deposit is dependent on many factors, including preheat and interpass temperatures intended to be used. The user of this information must make certain that, for the suggested electrode that is selected, the preheat and interpass temperatures will be proper for the application. Suggested filler metals in this Selector Guide do not always consider notch toughness (example Charpy V-Notch properties) requirements. Not all welding products are required to have minimum specified levels of notch toughness. If code, specifications, or contract documents require notch toughness, electrode selection should be limited to those products that meet the specific application requirements

### Customer Assistance Policy

The business of The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for advice or information about their use of our products. We respond to our customers based on the best information in our possession at that time. Lincoln Electric is not in a position to warrant or guarantee such advice, and assumes no liability, with respect to such information or advice. We expressly disclaim any warranty of any kind, including any warranty of fitness for any customer's particular purpose, with respect to such information or advice. As a matter of practical consideration, we also cannot assume any responsibility for updating or correcting any such information or advice once it has been given, nor does the provision of information or advice create, expand or alter any warranty with respect to the sale of our products.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying this type of fabrication methods and service requirements.

Subject to Change - This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.

# FILLER METAL SELECTOR GUIDE



Due to space consideration, these technical supporting notes are listed here. Each is tied to a code used in the body of the tables which comprise the remainder of this book. The notes and codes are listed below and may be used t reference additional information regarding recommended Lincoln consumables for each applications. Please be sure to use the notes as an aid in selecting Lincoln consumables.

## SMAW

- (1) Any E70X8 electrode may be used. Excalibur 7018, Jet-LH 78, and Excalibur 7018-1, are preferred over Jetweld LH-70 for most pipe and out-of-position welding. Jetweld LH-3800 can be used in place of E7018's for flat and horizontal fillet, lap, and flat butt welds.
- (2) Almost any E60XX or E70XX electrodes can be used. First, select electrode based on the joint requirements. If code, specifications, or contract documents require notch toughness electrode selection should be limited to those that meet the specific application requirements.
- (3) Almost any E70XX electrode can be used. First, select electrode based on the joint requirements. If code, specifications, or contract documents require notch toughness, electrode selection should be limited to those that meet the specific application requirements.
- (4) Best Electrodes are Fleetweld 5P, 5P+, 35 or 35LS.
- (5) Best Electrodes are Fleetweld 35, 180, 7, 37 or 47.
- (6) When resistance to atmospheric corrosion and matching weathering characteristics are needed (such as on unpainted structures), use Excalibur 8018-C3 MR (1% Ni). The second choice for multipass welds is Excalibur 8018-C1 MR (2-1/4% Ni). For single pass welds, multipass welds which are not exposed, and multipass welds which do not require resistance to atmospheric corrosion and matching weathering characteristics, any E7018 electrode may be used.
- (7) Fillet welds are frequently made with Excalibur 7018, Excalibur 7018-1, Jetweld LH-70, Jet-LH 78 or Excalibur 8018-C3.
- (8) Jetweld LH-70 for fillets or Excalibur 8018-C3 are recommended for general purpose welding these steels. Jetweld LH-90 can be used, particularly if the weldment is to be precipitation hardened or high weld strength is required.
- (9) Use Jet-LH-8018-C1 or, Excalibur 7018-1, when high impact properties (CVN) down to -75° F are required.
- (28) Use of Shield-Arc 90 should be limited to 3/8" maximum wall thickness.

## SAW

- (10) For single pass applications, any flux/wire combination meeting an AWS F7AX classification per AWS specification A5.17 may be used. Typically, for single pass applications, active fluxes such as 760, 761, 780 and 781 are recommended. 860, 865, 960 and 980 fluxes may also be suitable for single pass applications. The following flux/wire combinatins are classified under A5.17 and are recommended: 760/L-50, 760/L-61, 761/L-60, 761/L-61, 780/L-60, 781/L-50, 781/L-60, 781/L-61, 860/L-50, 860/L-61, 865/L-50, 865/L-61, 960/L-50, 960/L-61, 980/L-50, 980/L-61, & 980/LC-72. Refer to Lincoln Bulletin C5.10 for flux operability information.
- (11) For multiple pass applications, any flux/wire combination meeting an AWS F7AX classification per AWS specification A5.17 may be used. Typically, for multiple pass applications, neutral fluxes such as 860, 865, 880M, 882, 8500 and MIL 800-H are recommended. 960 and 980 fluxes may also be suitable for multiple pass applications. The following flux/wire combinations are classified under A5.17 and are recommended: 8500/L-50, 8500/L-61, 8500/L-S3, 860/L-50, 860/L-61, 860/L-S3, 865/L-50, 865/L-61, 880M/L-50, 880M/L-56, 880M/L-S3, 882/L-50, 882/L-56, 882/L-61, 882/L-S3, 960/L-50, 960/L-61, 980/L-50, 980/L-61, 980/LC-72, and MIL 800-H/L-S3. Refer to Lincoln Bulletin C5.10 for flux operability information.
- (12) 880/LAC-M2, 880M/LAC-M2.
- (13) MIL 800-H/LA-90, MIL 800-H/LA-100, 880M/LA-100, 880M/LA-92.
- (14) 882/LAC-Ni2, 880M/LA-90, 980/LAC-Ni2.

(15) When resistance to atmospheric corrosion and matching weathering characteristics are needed (such as on unpainted structures), use 960/LA-75, AXXX10/L-61 or 880, 880M, 882/LAC Ni2. For single pass welds, multipass welds which are not exposed, and multipass welds which do not require resistance to atmospheric corrosion and matching weathering characteristics, other filler metal combinations may be used.

(26) 880, 880M/LAC B2 may be used in place of the listed Flux/Wire combinations for most applications.

(31) Filler metals suitable for undermatching strength applications use A709, Grades 70W and HPS 70W and A852 are: MIL 800-HPNi/LA-75, 860/LA-75 and 960/LA-75.

(32) 780 flux is recommended for circumferential applications because of its faster freezing slag.

(33) 781 flux is recommended for making high speed, single pass welds on clean plate and sheet steel.

(34) 761, 780, 860/L-70. 761 and 780 are recommended for single pass applications. 860 is recommended for multipass welds.

## GMAW

- (16) SuperArc L-50, SuperGlide S3, SuperArc L-54, SuperArc L-56, SuperGlide S6, Metalshield MC-6 or MC-710XL.
- (29) Use LA-75 when resistance to atmospheric corrosion and matching weathering characteristics are needed. If the steel is to be painted and atmospheric corrosion resistance and matching weathering characteristic are not need, SuperArc L-50, L-54, L-56, SuperGlide S3, S6, Metalshield MC-6 or MC-710XL may be used. LA-75 is certified to meet 80 ksi min. tensile strength with 98% Ar/2% O<sub>2</sub> shielding gas. LA-75 with 75-90% Ar/balance CO<sub>2</sub> shielding gas meets a 70 ksi min. tensile strength.

## FCAW-S

- (17) Any Innershield electrode may be used, with the following restrictions:
  1. Innershield electrodes are not required to have specified levels of notch toughness. If code, specifications, or contract documents require notch toughness, an electrode should be selected to meet the specific requirements.
  2. .068", 5/64" & 3/32" dia. NR-211-MP are restricted to maximum 1/2" thick carbon steel. .035" & .045" dia. NR-211-MP are restricted to maximum 5/16" thick carbon steel.
  3. NR-1, NR-5, and NR-152 are typically used for high speed applications on carbon steel up to a maximum of 3/16" thick. NR-131 is designed for high speed, single pass welding on 12 gauge and thicker steels.
- (18) Innershield: NR-203MP, NR-203 Ni(1%), NR-232, NR-305, NR-311 Ni. (Exception: NR-311 Ni is not approved for use with any A709 grade when AASHTO/AWS D1.5 is applicable.)
- (19) Innershield: NR-203 Ni(1%).
- (21) For vertical down applications, NR-207 or NR-207-H are the best choices. For vertical up applications, the NR-203-XX series is the best choice.
- (22) When resistance to atmospheric corrosion and matching weathering characteristics are needed, use NR-203 Ni(1%). If the steel is to be painted and atmospheric corrosion resistance and matching weathering characteristic are needed, any E7XT-6, or -8 may be used.

## FCAW-G

- (23) Outershield 70, 70-H, XLH70, 71, 71M, 71 Elite.
- (24) Outershield 81K2-H, 81Ni1-H
- (25) When resistance to atmospheric corrosion and matching weathering characteristics are needed (such as on unpainted structures), use 81K2-H or 81Ni1-H. For single pass welds, multipass welds which are not exposed, and multipass welds which do not require resistance to atmospheric corrosion and matching weathering characteristics, any E7XT-1, -5, or -9 may be used.



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A27	Carbon Steel Castings	All	60-70	30-40
A36	Structural-36,000 Min. Yield Strength	All, Carbon Steel #	58-80	36 min
A53	Pipe-Black, Hot dipped	Type E & S, Grade A Type E & S, Grade B Type F	48 min 60 min 48 min  70 min	30 min 35 min 30 min  36 min
A105	Forgings, for Piping			
A106	Pipe	A & B C	48 & 60 min 70 min	30 & 35 min 40 min
A131	Structural Steel for Ships (Recommendations are based on strength req'ts. Impact Test Temp. req'ts are as follows: Grades B & AHxx @ +32°F, Grades D & DS @ +14°F, Grades DHxx @ -4°F, & Grades CS, E & EHxx @ -40°F. EH40 and FHxx grades are normalized, thermo-mechanical control processed, or quenched & tempered. FHxx grades impact test temp are -76°F	A, B, D, DS, CS, E (Gr A Imp't Test Temp @ +68°F) AH32, DH32 & EH32 AH36, DH36 & EH36 AH40, DH40 & EH40 FH32 FH36 FH40	58-75  64-85 71-90 74-94 64-85 71-90 74-94	34 min  46 min 51 min 57 min 46 min 51 min 57 min
A134	Pipe	See A36, A283, A285, or A570		
A135	Pipe, Electric-Resistance-Steel (5.563" Max. Dia.)	A B	48 min 60 min	30 min 35 min
A139	Pipe, Electric-Fusion (Arc)-Welded	A B C D E	48 min 60 min 60 min 60 min 66 min	30 min 35 min 42 min 46 min 52 min
A148	Castings-Structural	80-40 & -50 90-60  105-85 & 115-95 150-135	80 min 90 min  105 & 115 min 150 min	40-50 min 60 min  85 & 95 min 135 min
A161	L Carbon & C-Mo Still Tubes for Refinery Serv. @ Elevated Temperature (Discontinued in 1999, replaced by A192)	Low Carbon	47 min	26 min
A178	Electric-Resistance-Welded Carbon Steel & C-Mn Boiler Tubes (5" Max Dia.)	T1 (.5% Mo)  A (Low Carbon) C (Medium Carbon) D (Carbon-Manganese)	55 min  47 min 60 min 70 min	30 min  26 min 37 min 40 min
A179	Heat Exchanger (1/8"-3" Dia.)		47 min	26 min
A181	Forgings, for General-Purpose Piping	Class 60 Class 70	60 min 70 min	30 min 36 min
A182	High Temp. Fittings, Flanges, Valves, etc.	F1 (.5% Mo) F2 (.5% Cr, .5% Mo)  F11, Class 1&2 (1.25%Cr,.5%Mo) F11, Class 3 (1.25%Cr,.5%Mo) F12, Class 1 (1% Cr, .5% Mo) F12, Class 2 (1% Cr, .5% Mo) F21 (3% Cr, 1 Mo) F22, Class 1 (2.25 Cr, 1% Mo) F22, Class 3 (2.25 Cr, 1% Mo)	70 min 70 min  60 min & 70 min 75 min 60 min 70 min 75 min 60 min 75 min	40 min 40 min  30 min & 40 min 45 min 30 min 40 min 45 min 30 min 45 min
A192	Boiler Tube for High Pressure Service	7" Max Dia.	47 min	26 min
A199	Heat Exchanger Tubes (1/8"-3" Dia.)	T4 (2.5% Cr, .5% Mo) T11 (1.25% Cr, .5% Mo) T22 (2.25% Cr, 1% Mo)	60 min 60 min 60 min	25 min 25 min 25 min
A200	Refinery Still Tubes (2"- 9" Dia.) (Discontinued in 1999, replaced by A213)	T4 (2.5% Cr, .5% Mo)  T11 (1.25% Cr, .5% Mo)  T22 (2.25% Cr, 1% Mo)	60 min 60 min 60 min	25 min 25 min 25 min
A202	Pressure Vessel Cr-Mn-Si	A (.5% Cr) B (.5% Cr)	75-95 85-110	45 min 47 min
A203	Pressure Vessel - Alloy Steel, Ni (Normalized) CVN Test Temp. shall be a matter of agreement between purchaser & supplier, may be as low as -100°F, which may change recommendations.	A & D (2.25% Ni & 3.5% Ni) B & E (2.25% Ni & 3.5% Ni) F (3.5% Ni)	65-85 70-90 (</= 2") 80-100 > 2") 75-95	37 min 40 min (</= 2") 55 min > 2") 50 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
(1)	(10), (11)	(16)	(18)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
Excalibur 7018, LH-78 MR	(10), (11), (32)	(16)	(21)	(23)
(2)	(10), (11)	(16)	(21)	(23)
(2)	(10), (11)	(16)	(21)	(23)
(1), (2)	(10), (11)	(16)	(18)	(23)
(1), (3)	(10), (11)	(16)	(18)	(23)
(1), (3)	(10), (11)	(16)	(18)	(23)
(1)	(10), (11)	(16)	(18)	(23)
LH-8018-C1 MR, Excalibur 8018-C1 MR	880,880M/LAC Ni2	LA75		
LH-8018-C1 MR, Excalibur 8018-C1 MR	880,880M/LAC Ni2	LA75		
LH-8018-C1 MR, Excalibur 8018-C1 MR	880,880M/LAC Ni2	LA75		
(2), (4)		(16)	(21)	(23)
(2), (4)		(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
(2), (4)	(10), (11), (32)	(16)	(21)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	860,960/LA75, 860/LA85	LA75		
LH-90 MR, Jet-LH 8018-B2 MR,	880M/LA100, 8500/LA-82	LA90, LA100, MC900		
Excalibur 9018-M MR		LA100, MC-1100		
LH-110M MR, LH100M1 MR	880, 880M/LAC-M2, 882/LA-82, MIL800H/LA-100, MIL800H/LA-82			
Excalibur 7018, 7018-1, LH-78 MR, (4)	(10), (11), (32)	(16)	(21)	(23)
SA-85, Excalibur 7018-A1	(34), (32)	LA90	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (4)		(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (4)		(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR		(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (4)		(16)		
Excalibur 7018, 7018-1, LH-78 MR, Excalibur 7018, 7018-1, LH-78 MR	(10), (11), (32)	(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, Excalibur 7018, 7018-1, LH-78 MR	(10), (11), (32)	(16)	(21)	(23)
SA-85, Excalibur 7018-A1 LH-90 MR, Jet-LH 8018-B2 MR	(34), (32) MIL800-H, 880M, 882/LA92, (26)	LA90		
LH-90 MR, Jet-LH 8018-B2 MR	MIL800-H, 880M, 882/LA92, (26)			
LH-90 MR, Jet-LH 8018-B2 MR	MIL800-H, 880M, 882/LA92, (26)			
LH-90 MR, Jet-LH 8018-B2 MR	MIL800-H, 880M, 882/LA92, (26)			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
(2), (4)	(10), (32)	(16)	(21)	(23)
Jet-LH 9018-B3 MR				
LH-90 MR, Jet-LH 8018-B2 MR				
Jet-LH 9018-B3 MR				
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92, (26)			
LH-90 MR, Jet-LH 8018-B2 MR	MIL800-H, 880M, 882/LA92, (26)			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	LA75, (16)		
LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	LA100, MC1100		
LH-8018-C1 MR, Excalibur 8018-C1 MR	(10), (11)	LA75		
LH-8018-C1 MR, Excalibur 8018-C1 MR	(10), (11)	LA75		
LH-8018-C1 MR, Excalibur 8018-C1 MR	(10), (11)	LA75		
LH-8018-C1 MR, Excalibur 8018-C1 MR	(10), (11)	LA75		



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A204	Boiler & Pressure Vessel (.5% Mo) Plates > 1-1/2" Normalized	A B C	65-85 70-90 75-95	37 min 40 min 43 min
A209	C-Mo Boiler Tubes (1/2" - 5" Dia.)	T1, T1a, & T1b	55, 53, & 60 min	30, 28, & 32 min
A210	Carbon Steel Boiler Tubes (1/2" - 5" Dia.)	A-1 C	60 min 70 min	37 min 40 min
A211	Spiral Welded Pipe (Discontinued in 1993)	See A570		
A213	Boiler Tubes (1/8" - 5" Dia.)	T2 (.75% Cr, .5% Mo) T11 (1.25% Cr, .5% Mo) T12 (1% Cr, .5% Mo) T17 (1% Cr) T21 (3% Cr, 1% Mo) T22 (2.25% Cr, 1% Mo)	60 min 60 min 60 min 60 min 60 min 60 min	30 min 30 min 30 min 30 min 30 min 30 min
A214	Heat-Exchanger Tubes (3" Max. Dia.)			
A216	Carbon Steel Castings - High Temp.	WCA WCB WCC	60-85 70-95 70-95	30 min 36 min 40 min
A217	Steel Castings, High Temp.	WC1 (.5% Mo) WC4(.75%Cr,.5%Mo, .9%Ni) WC5(.75%Cr,1%Mo, .8% Ni) WC6 (1.25% Cr, .5% Mo) WC9 (2.5% Cr, 1% Mo) WC11 (1.25% Cr, .5% Mo)	65-90 70-95 70-95 70-95 70-95 80-105	35 min 40 min 40 min 40 min 40 min 50 min
A225	Pressure Vessel, Mn-V- .5% Ni	C (> 2" Normalized) D (Normalized)	105-135 80-105	70 min 60 min
A226	High-Pressure Service (5" Max. Dia.) (Discontinued in 1997)		47 min	26 min
A234	Wrought Welding Fittings for Moderate & Elevated Temperatures	WPB	60-85	35 min
		WPC  WP1 (.5% Mo) WP11, Class 1(1.25% Cr,.5% Mo) WP11, Class 2(1.25%Cr,.5%Mo) WP11, Class 3 (1.25%Cr,.5%Mo) WP12, Class 1 (1%Cr,.5% Mo) WP12, Class 2 (1%Cr,.5% Mo) WP22, Class 1(2.25% Cr,1% Mo) WP22, Class 3 (2.25% Cr,1% Mo)	70-95  55-80 60-85 70-95 75-100 60-85 70-95 60-85 75-100	40 min  30 min 30 min 40 min 45 min 30 min 40 min 30 min 45 min
A242	High Strength, Low Alloy Structural-Cu (.2% Cu min.) Groups listed are for Structural Shapes. For Plates & Bars, Tensile requirements are based on thickness.	Shapes-Group 1 & 2, (Plates 3/4" & less) Shapes-Group 3, (Plates Over 3/4 to 1-1/2") Shapes-Group 4 & 5, (Plates Over 1-1/2 to 4')	70 min 67 min 63 min	50 min 46 min 42 min
A250	C-Mo Tubes (1/2" - 5" Dia.)	T1 (.5% Mo) T1a (.5% Mo) T1b (.5% Mo) T2 (.75% Cr, .5% Mo) T11 (1.25% Cr, .5% Mo) T12 (1% Cr, .5% Mo) T22 (2.25% Cr, 1% Mo)	55 min 60 min 53 min 60 min 60 min 60 min 60 min	30 min 32 min 28 min 30 min 30 min 30 min 30 min
A252	Steel Pipe Piles	1  2  3	50 min  60 min  66 min	30 min  35 min  45 min
A266	Pressure Vessel forgings	1 2 & 4 3	60-85 70-95 75-100	30 min 36 min 37.5 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
SA-85, LH-78 MR, Excalibur 7018-A1 (2), (4) SA-85, LH-78 MR, Excalibur 7018-A1	(34) (34) (34)	LA90 LA90 LA90 LA90, (16)	(21)	(23)
LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR		LA90		
Jet-LH 9018-B3 MR				
Excalibur 7018, 7018-1, LH-78 MR		(16)		
(1) (1) (1)	(10), (11) (10), (11) (10), (11)	LA75, LA90 LA75, LA90 LA75, LA90	(18) (18) (18)	(23) (23) (23)
LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR LH-90 MR, Jet-LH 8018-B2 MR	(10), (11) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA92, (26)	LA90		
LH-110M MR LH-8018-C3 MR, Excalibur 8018-C3 MR	(12) 860, 960/LA75	MC1100 LA75		(24)
Excalibur 7018, 7018-1, LH-78 MR, (4)		(16)	(21)	(23)
Excalibur 7018, LH-78 MR, (4)	(10), (11)	(16)	(18)	(23)
Excalibur 7018, LH-78 MR, (4) SA-85, Excalibur 7018-A1 LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR Jet-LH 9018-B3 MR	(10), (11) (34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93	(16) LA90	(18)	(23)
(1), (6) (1), (6) (1), (6)	(10), (11), (15) (10), (11), (15) (10), (11), (15)	(29) (29) (29)	NR-203Ni1% NR-203Ni1% NR-203Ni1%	(25) (25) (25)
SA-85, Excalibur 7018-A1 SA-85, Excalibur 7018-A1 SA-85, Excalibur 7018-A1 LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR		LA90 LA90 LA90		(23) (23) (23)
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4)	(10), (11), (32) (10), (11), (32) (10), (11), (32)	(16) (16) (16)	(17) (17) (17)	(23) (23) (23)
(1) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11) (10), (11) (10), (11)	(16) (16) (16)	(18) (18) (18)	(23) (23) (24)

## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A283	Structural Plates Storage Tank Construction	A	45-60	24 min
		B	50-65	27 min
		C	55-75	30 min
		D	60-80	33 min
A284	C-Si Steel Plates (Discontinued 1994)	C & D	60 min	30 & 33 min
A285	Pressure Vessel Plate	A	45-60	24 min
		B	50-70	27 min
		C	55-75	30 min
A299	Pressure Vessel Plate Mn-Si		75-95	42 min
A302	Pressure Vessel Plates > 2" Normalized Mn-Mo (Grade A & B) Mn-Mo-Ni (Grade C & D)	A (.5% Mo)	75-95	45 min
		B (.5% Mo)	80-100	50 min
		C & D (.5% Mo, .6% Ni) & (.5% Mo, .8% Ni)	80-100	50 min
A328	Steel Sheet Piling		70 min	39 min
A333 & A334	Low Temperature Pipe	1 (CVN's @ -50° F, 13 ft-lb)	55 min	30 min
		6 (CVN's @ -50° F, 13 ft-lb)	60 min	35 min
		7 (CVN's @ -100° F, 13 ft-lb)	65 min	35 min
A335	High Temperature Pipe	P1 (.5% Mo)	55 min	30 min
		P2 (.75% Cr, .5% Mo)	55 min	30 min
		P11 (1.25% Cr, .5% Mo)	60 min	30 min
		P12 (1% Cr, .5% Mo)	60 min	32 min
		P15 (1.4% Si, .5% Mo)	60 min	30 min
		P22 (2.25% Cr, 1% Mo)	60 min	30 min
A336	Pressure Vessel forgings, F11-C1, C2, & C3 (1.25% Cr, .5% Mo), F12 (1% Cr, .5% Mo), F21-C3 (3% Cr, 1% Mo), F22-C3 (2.25% Cr, 1% Mo)	F1 (.5% Mo)	70-95	40 min
		F11-C2, F11-C3, F11-C1, F12	70-100	30-45 min
		F21-C3, F21-C1, F22-C3, F22-C1	60-100	30-45 min
A350	Low Temp. forgings, etc., Requiring Notch Toughness Testing for Piping Components	LF1 (CVN's @ -20° F, 13 ft-lbs)	60-85	30 min
		LF2 (CVN's @ -50° F, 13 ft-lbs)	70-95	36 min
		LF5 Class 1 (CVN's @ -75° F)	60-85	30 min
		LF5 Class 2 (CVN's @ -75° F)	70-95	37.5 min
		LF 6 Class 1 (CVN's @ -60° F)	66-91	52 min
		LF 6 Class 2 (CVN's @ -60° F)	75-100	60 min
		LF 6 Class 3 (CVN's @ -0° F)	75-100	60 min
A352	Low Temp. Castings for Pressure Containing Parts, Low Temperature Service, CVN's for LCA tested @ -25° F, CVN's for LCB & LCC tested @ -50° F	LCA (.5% Ni, .5% Cr, .2% Mo)	60-95	30-40 min
		LCB & LCC (.5% Ni, .5% Cr, .2% Mo)	60-95	30-40 min
		LC1 (.5% Mo)	65-90	35 min
		LC2 (2.5% Ni)	70-95	40 min
A356	Steam Turbine Castings	1	70 min	36 min
		2 (.5% Mo)	65 min	35 min
		5, 6 (.5% & 1.25% Cr, .5% Mo)	70 min	40 & 45 min
		8, 9 (1% Cr, 1% Mo, V)	80 & 85 min	50 & 60 min
		10 (2.25% Cr, 1% Mo)	85 min	55 min
A366	Carbon Steel Sheets (Discontinued 8/00, replaced with A1008)	Type A, B, & C	—	—
A369	High Temperature Forged & Bored Pipe	FPA	48 min	30 min
		FPB	60 min	35 min
		FP1 (.5% Mo)	55 min	30 min
		FP2 (.75% Cr, .5% Mo)	55 min	30 min
		FP11 (1.25% Cr, .5% Mo)	60 min	30 min
		FP12 (1% Cr, .5% Mo)	60 min	30 min
		FP21 (3% Cr, 1% Mo)	60 min	30 min
		FP22 (2.25% Cr, 1% Mo)	60 min	30 min
A372	Pressure Vessel forgings, thin-walled, Type IV (.2% Mo), Type V (1% Cr, .2% Mo)	Grade A	60-85	35 min
		Grade B	75-100	45 min
		Grade C, Grade E (Class 55)	90-115 & 85-110	55 min
		Grade D, Grade E (Class 65)	105-130	65 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	(16)	(18)	(23)
	(34)	(16)	(18)	(23)
	(34), 880M/L56	LA75		(24)
	MIL 800-H/LA82	LA75, LA100		(24)
(1)	(10), (11)	(16)	(17)	(23)
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	882/L50, 880M/L50, 8500/L-S3	LA75	NR-207	(24)
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	882/L50, L-S3	LA75	NR-207	(24)
LH-8018-C1 MR, Excalibur 8018-C1 MR				
SA-85 LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR SA-85, Excalibur 7018-A1 Jet-LH 9018-B3 MR	(34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93	LA90		
LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR	(34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93	LA90		(23)
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	(16)	(17)	(23)
Excalibur 7018-1, LH-8018-C3 MR, Excalibur 8018-C3 MR	880M/L56, L50, L-S3, 882/L50, L-S3, 8500/L-S3, L50	LA75	NR-207	(24)
LH-8018-C1 MR, Excalibur 8018-C1 MR LH-8018-C1 MR, Excalibur 8018-C1 MR	880M/LA75, L50, 8500/L-S3 880M/LA75, L50, 8500/L-S3 880M/LA75, L50, 8500/L-S3 880M/LA75, L50, 8500/L-S3	LA75 LA75 LA75 LA75	NR-207 NR-207 NR-207 NR-207	81K2-H 81K2-H 81K2-H 91K2-H
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	LA75	NR-207	91K2-H
(1) Excalibur 7018-1	(10), (11) 880M/LA75 860/L70 880, 880M/LAC Ni2	(16) LA75 LA90	(18) NR-207	(23) (24) (24)
LH-8018-C1 MR, Excalibur 8018-C1 MR				
(3) LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR	(10), (11) (34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93	(16) LA90	(18)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(4) SA-85, Excalibur 7018-A1 LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR Jet-LH 9018-B3 MR	(10), (34) (10), (34) (34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA93	(16) (16) LA90	(21) (21)	(23) (23)
(1) LH-8018-C3 MR LH-110M MR LH-110M MR	(10), (11) (10), (11) 880M/LA90 (12)	(16) (16) LA90 MC1100	(17) (18)	(23) (23) (24)

## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A381	High Pressure Pipe for Transmission Systems	Y35	60 min	35 min
		Y42	60 min	42 min
		Y46	63 min	46 min
		Y48	62 min	48 min
		Y50	64 min	50 min
		Y52	66 min	52 min
		Y56	71 min	56 min
		Y60	75 min	60 min
A387	Pressure Vessel Plate, Cr-Mo Grades 2, 11, & 12-.5%Mo (Class 1 Lower Tensile) (Class 2 Higher Tensile)	2 (.75% Cr), 11 (1% Cr), & 12 (1.25% Cr)	55-85, 65-90	30 min, 45 min
		22 (2.25% Cr, 1% Mo)	60-85, 75-100	30 min, 45 min
		21 (3% Cr, 1% Mo)	60-85, 75-100	30 min, 45 min
		C23 (1.25% Cr, .5% Mo)	70 min	40 min
		C24 (1% Cr, 1% Mo)	80 min	50 min
		P24 (1% Cr, 1% Mo)	80 min	50 min
		A, B, C, & D	45, 50, 55, & 60 min	25, 30, 33, & 35 min
		E, F, & G	65, 70, & 75 min	38, 42, & 45 min
A405	High Temperature Pipe	WPL6 (CVN's @-50° F, 25 Ft-Lbs)	60-85	35 min
		WPL9 (CVN's @-100° F, 25 Ft-Lbs)	63-88	46 min
A414	Pressure Vessel Sheet {Grades A,B,C, & D - Max. Ten. = Min. Ten + 15 ksi, Grades E,F, & G- Max. Ten. = Min. Ten + 20 ksi}	1 (.75% Cr, .5% Ni)	60 min	37 min
		2 (.75% Ni)	60 min	37 min
A420	Low Temperature Fittings	CP1 (.5% Mo)	65 min	35 min
		CP2 (.75% Cr, .5% Mo)	60 min	30 min
		CP11 (1.25% Cr, .5% Mo)	70 min	40 min
		CP12 (1% Cr, .5% Mo)	60 min	30 min
		CP15 (1.4% Si, .5% Mo)	60 min	30 min
		CP21 (3% Cr, 1% Mo)	60 min	30 min
		CP22 (2.25% Cr, 1% Mo)	70 min	40 min
A441	Discontinued 1989, Replaced by A572			
A442	Plate with Improved Transition Properties	55	55-75	30 min
		60	60-80	32 min
A455	Pressure Vessel Plate C-Mn		70-95	35-38 min
A469	Vacuum-Treated Steel forgings	Class 1	75 min	35 min
		Class 2 (2.5% Ni, .3% Mo)	80 min	55 min
		Class 3 (2.5% Ni, .3% Mo)	90 min	70 min
A470	Alloy Steel forgings	Class 1	75 min	40 min
		Class 2 (3.5% Ni, .75% max Cr)	80 min	55 min
		Class 3, 9, & 5	90 min & 90-110	70 min
		Class 4, & 6, 8	105 min & 105-125	85 min
A486	Highway Bridge Castings (Discontinued 1989)			
A487	Castings-Pressure Service 1's V, 2's MnMo, 4's NiCrMo, 6's MnNiCrMo 8's (2.25% Cr, 1% Mo) & 9's (1% Cr, .3% Mo) 10's, 11's, 12's NiCrMo 13's & 14's NiMo, 16A Low C, MnNi	1A,1B,1C,2A,2B,2C,4A,4C,9C,13A 10A, 4B, 8B, 13B	85-115 100-130	53-65 min 70-85 min
		11A, 12A 9D,11B,12B	70-95 100-130	40 min 70-85
		10B,14A 16A	120-145 70-95	95-100 min 40 min
A498	Heat-Exchanger Tubes	See A199, A213 & A334		
A500	Structural Tubing	A	45 min	45 min
		B	58 min	42 min
		C	62 min	46 min
		D (SR 1100 F for 1hr/in., .5hr min.)	58 min	36 min

**FILLER METAL SELECTOR GUIDE**

<b>SMAW</b>	<b>SAW</b>	<b>GMAW**</b>	<b>FCAW-S</b>	<b>FCAW-G**</b>
Excalibur 7018, 7018-1, LH-78 MR, (4)	860/L60, L61	(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (4)	860/L60, L61	(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (4)	860/L60, L61	(16)	(21)	(23)
Excalibur 7018, 7018-1, LH-78 MR, (2)	860/L60, L61	(16)	(21)	(23)
SAHYP+, Excalibur 7018, 7018-1,, LH-78 MR	860/L60, L61	(16)	(21)	(23)
SAHYP+, Excalibur 7018, 7018-1, LH-78 MR	860/L60, L61	(16)	(21)	(23)
SA70+, SA80, LH-78 MR	860/L60, L61	(16)	(21)	(23)
SA70+, SA80, SAHYP+, LH-D80, LH-D90, Pipeliner 8P+	860/L60, L61	(16)	(21)	(24)
SA70+, SA80, LH-D80, LH-D90, Pipeliner 8P+	860/L60, L61	(16)	(21)	(24)
LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93			
LH-90 MR Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92, (26)	LA90		
(2), (5) (1)	(10), (11), (33) (10), (11), (33)	(16) (16)	(17) (17)	(23) (23)
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C1 MR, Excalibur 8018-C1 MR	882/L56 880M/LAC-Ni2	LA75	NR-207	81K2-H
LH-90 MR LH-8018-C3 MR, Excalibur 8018-C1 MR		(16) LA75	NR-203Ni1%	81Ni1-H
SA-85, Excalibur 7018-A1 LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR LH-90 MR, Jet-LH 8018-B2 MR SA-85, Excalibur 7018-A1 Jet-LH 9018-B3 MR Jet-LH 9018-B3 MR	(34) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA93	LA90		
(1) (1)	(10), 860/L61, 880M/L50 (10), 860/L61, 880M/L50	(16) (16)	(18) (18)	(23) (23)
LH-8018-C3 MR, (1), Excalibur 8018-C3 MR	(10), (11)	(16)	(18)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C1 MR, Excalibur 8018-C1 MR Excalibur 9018-M MR	(10), (11) 880, 880M/LAC Ni2 880MLA100	L56, SGS-6 LA100	(18)	(23) 91K2-H
Excalibur 8018-C1, 8018-C3 MR, 9018-M MR LH-8018-C1 MR, Excalibur 8018-C1 MR	(10), (11) 880, 880M/LAC Ni2 882/LAC Ni2	(16)	(18)	(23)
Excalibur 8018-C1, 8018-C3 MR, 9018-M MR LH-110M MR	(12)	LA100, MC900, MC1100		
Excalibur 8018-C1, 8018-C3 MR, 9018-M MR LH-110M MR	860, 880M/LA100 (12)	LA100, MC1100		
LH-90 MR, Jet-LH 8018-B2 MR LH-110M MR	(10), (11) (12)	(16) LA100, MC1100	(18)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	860, 960/LA75	LA75	NR-203 Ni1%	81Ni1-H
(2) (2) (2) Excalibur 7018, 7018-1, LH-78 MR	(10), (11) (10), (11) (10), (11) (10), (11)	(16) (16) (16) (16)	(17) (17) (17) (16)	(23) (23) (23) (23)



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A501	Structural Tubing		58 min	36 min
A508	Pressure Vessel forgings, Quenched & Tempered	1 & 1A 2-C1 & 3 (.75% Ni, .5% Mo) 2-C2, 3-C2 (.75% Ni, .5% Mo) 4N-C3 (3.25% Ni, 1.75% Cr, .5% Mo) 4N-C1 & 5-C1 (3.25% Ni, 1.75% Cr, .5% Mo) 4N-C2 & 5-C2 (3.25% Ni, 1.75% Cr, .5% Mo) 22-C3 (2.25% Cr, 1% Mo)	70-95 80-105 90-115 90-115 105-130 115-140 85-110	36 min 50 min 65 min 70 min 85 min 100 min 55 min
A514	Quenched & Tempered Plate	All Grades > 2 1/2" All Grades 2 1/2" & under	100-130 110-130	90 min 100 min
A515	High Temperature Pressure Vessel Plate	60 65 & 70	60-80 65-85 & 70-90	32 min 35 min & 38 min
A516	Pressure Vessel Plate	55 & 60 65 & 70	55-75 & 60-80 65-85 & 70-90	30 min & 32 min 35 min & 38 min
A517	Pressure Vessel, Quenched & Tempered	All Grades 2 1/2" & under All Grades 2 1/2" - 6"	115-135 105-135	100 min 90 min
A521	Closed Die forgings	AA,AB,CE,CF & CF1 AC, AD & CG CA, CC & CC1 AE	75 min to 85 min 82 min to 96 min 60 min to 66 min 95 min to 105 min	37 min to 55 min 48 min to 58 min 30 min to 33 min 75 min to 80 min
A523	High Pressure Pipe (4" -12" Dia.)	A B	48 min 60 min	30 min 35 min
A524	Seamless Carbon Steel Pipe, for Atmospheric & Lower Temps.	I II	60-85 55-80	35 min 30 min
A529	High Strength C-Mn Steel of Structural Quality	42 50 & 55	60-85 70-100	42 min 50 min & 55 min
A533	Pressure Vessel, Quench. & Temp. Mn-Mo-Ni Type A (.50% Mo) Type B (.50% Mo,.55% Ni) Type C(.50%Mo,.85%Ni) Type D(.50%Mo.30%Ni)	Class 1, Type A, B, C, & D Class 2, Type A, B, C, & D Class 3, Type A, B, C, & D	80-100 90-115 100-125	50 min 70 min 83 min
A537	Pressure Vessel Plate C-Mn-Si	1 (Normalized) </= 2.5" 1 (Normalized) >2.5" - 4" 2 & 3 Quen & Temp </= 2.5" 2 & 3 Quen & Temp >2.5" - 4" 2 & 3 Quen & Temp >4" - 6"	70 min 65 min 80 min 75 min 70 min	50 min 45 min 60 min & 55 min 55 min & 50 min 46 min & 40 min
A539	Tubing for Gas & Oil Lines	2-3/8" Max. Dia., 1/8" Max. Thickness	45 min	35 min
A541	Pressure Vessel forgings, Quenched & Tempered Grades 2 & 3 (.5% Mo) Grade 4N, Class 3 (1.5% Cr, .5% Mo) Grade 11 Class 4 (1.25% Cr, .5% Mo) Grade 22 Classes 3, 4, & 5 (2.25% Cr, 1% Mo)	1, 1A 2 Class 1, & 3 Class 1 11 Class 4 2 Class 2, 3 Class 2 22 Class 4 22 Class 5 4N Class 3 22 Class 3	70-95 80-105 80-105 90-115 105-130 115-140 90-115 85-110	36 min 50 min 50 min 65 min 85 min 100 min 70 min 55 min
A542	Pressure Vessel Plates, Quenched & Tempered Type A & B (2.25%Cr, 1%Mo) Type C (3%Cr,1%Mo,+V,Ti,B)	Class 1, Type A, B, & C Class 2, Type A, B, & C Class 3, Type A, B, & C Class 4 & 4a, Type A, B, & C	105-125 115-135 95-115 85-110	85 min 100 min 75 min 55 min & 60 min
A543	Pressure Vessel Plate, Quenched & Tempered (1.5% Cr, .4%Mo) Type B 3% Ni, Type C 2.75% Ni	Class 1, Type B & C Class 2, Type B & C Class 3, Type B & C	105-125 115-135 90-115	85 min 100 min 70 min
A556	Seamless, Cold-Drawn Feedwater Heater Tubes (1-1/4" Max. Dia.)	A2  B2  C2	47 min  60 min  70 min	26 min  37 min  40 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
(2)	(10), (11)	(16)	(17)	(23)
(1) LH-110M MR LH-110M MR LH-110M MR	(10), (11) 882, 8500, MIL800-H/LA82 882, 8500, MIL800-H/LA82  (12)	(16)  LA100	(18)	(23)
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
LH-110M, (7)	(12)	LA100, MC1100		
LH-110M, (7)	(12)	LA100, MC1100		
(1) (1)	(10), (11) (10), (11)	(16) (16)	(18) (18)	(23) (23)
(1) (1)	(10), (11) (10), (11)	(16) (16)	(18) (18)	(23) (23)
(7) LH-110M MR, (7)	(12) (12)			
Excalibur 9018-M MR Excalibur 9018-M MR (1) LH-110M MR	960, 860/LA75, 860/LA85 (14) (10), (11) (12)	LA75 LA90 (16) LA100	(18)	81Ni1-H 91K2-H (23)
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4)	780/L60, L61  780/L60, L61	(16)  (16)	(21)  (21)	(23)  (23)
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4)	(10), (11)  (10), (11)	(16)  (16)	(17)  (17)	(23)  (23)
(1) (1)	(10), (11) (10), (11)	(16) (16)	(17) (17)	(23) (23)
LH-8018-C3, Excalibur 8018-C3 MR LH-110M, (4) LH-110M MR	882, 8500, MIL800-H/LA82 882, 8500, MIL800-H/LA82 8500, MIL800-H/LA82	LA75 LA90 LA100, MC1100		(24) 91K2-H
(1) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR (1), LH-8018-C3 MR, Excalibur 8018-C3 MR (2), (4)	(10), (11) (10), (11) (10), 882, 8500/LA85 MIL800-H/LA-71 MIL800-H/LA-71	(16) (16) LA75 (16) (16)	(17) (17) (18) (18)	(23) (23) (24) (24) (24)
(1) LH-8018-C3, Excalibur 8018-C3 MR LH-90 MR, Jet-LH 8018-B2 MR  LH-110M MR	(10), (11) (10), 880M/LA90 (10), (11) 882, 8500/LA82 (12)	(16) LA90 (16) LA100, MC900 MC1100  MC1100	(18)  (18)	(23) (24) (23) 91K2-H
Excalibur 9018-M MR	MIL800-H, 880M, 882/LA93	MC1100		
LH-110M MR	(12)	MC1100		
LH-110M MR	MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA93			
LH-110M, (7)	(12)	LA100, MC1100		
LH-110M MR	MIL800-H, 880M, 8500/LA100	LA100		91K2-H
Excalibur 7018, LH-78 MR, (4) Excalibur 7018, LH-78 MR, (4) Excalibur 7018, LH-78 MR		(16) (16) (16)		



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A557	Electric-Resistance Welded Feedwater Heater Tubes (1-1/4" Max. Dia.)	A2	47 min	26 min
		B2	60 min	37 min
		C2	70 min	40 min
A562	Pressure Vessel Plate, Carbon Steel, Mn-Ti, for Glass or Diffused Metallic Coatings		55-75	30 min
A569	Hot-Rolled Sheet, 0.15% Max C, (Discontinued 8/00, replaced with A1011)	Type A, B, & C	None Specified	None Specified
A570	Structural Sheet & Strip, Hot-Rolled Max. Thickness 0.229" (Discontinued 8/00, replaced with A1011)	30, 33, 36, 40, & 45 50 & 55	49,52,53,55,&60 min 65 & 70 min	30,33,36,40,&45 min 50 &55 min
A572	High Strength Structural Columbium-Vanadium	42	60 min	42 min
		50	65 min	50 min
		55	70 min	55 min
		60	75 min	60 min
		65	80 min	65 min
A573	Structural Plate of Improved Toughness	58	58-71 min	32 min
		65	65-77 min	35 min
		70	70-90 min	42 min
A587	Low Carbon Steel Pipe, Chem. Industry		48 min	30 min
A588	High Strength Structural, with Atmospheric Corrosion Resistance (Recommended consumables are the same regardless of thicknesses)	All Structural Shapes & Plates 4" & Under Plates over 4" to 5"	70 min	50 min
		Plates over 5"	67 min 63 min	46 min 42 min
A589	Seamless & Welded Carbon Steel Water-Well Pipe	Butt Welded	48 min	30 min
		A	48 min	30 min
		B	60 min	35 min
A592	Pressure Vessels, Quenched & Tempered, Forged Fittings	A (.75% Cr), E (1.75% Cr,.5% Mo), F (.5% Cr, .5% Mo)	Up to 2.5" 115-135 > 2.5" - 4' 105-135	Up to 2.5" 100 min > 2.5" - 4' 90 min
A595	Structural Tubing	A	65 min	55 min
		B	70 min	60 min
		C (Weather Resistant, Cu,Cr,Ni)	70 min	60 min
A606	Sheet, Hot & Cold Rolled, High-Strength, Low-Alloy, Atmospheric Corrosion Resistant	Hot Rolled [As Rolled & Annealed or Normalized] Cold Rolled [Cut Lengths & Coils]	70 & 65 min 65 min	50 & 45 min 45 min
A607	Sheet, High Strength, Low Alloy Co or V or Both Cold Rolled or Hot Rolled (Discontinued 8/00, replaced with A1008 & A1011)	45	60 min	45 min
		50, 55, & 60	65 & 70 min	50 & 55 min
		65	80 min	65 min
		70	85 min	70 min
A611	Structural Sheet (Discontinued 8/00, replaced with A1008)	A & B	42 & 45 min	25 & 30 min
		C Types 1 & 2	48 min	33 min
		D Types 1 & 2	52 min	40 min
		E (Full Hard Product)	82 min	80 min
A612	Pressure Vessel Plate for Low Temperature Service	0.5 & Under	83-105	50 min
		> 0.5	81-101	50 min
A615	Billet Steel Bars, Concrete Reinforcement (0.376"-2.257" Dia.)	40	70 min	40 min
		60	90 min	60 min
		75	100 min	75 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR		(16) (16) (16)		
Excalibur 7018, 7018-1, LH-78 MR	(10), (11)	(16)	(18)	(23)
(2)	(10), (11)	(16)	(17)	(23)
(2) (1)		(16) (16)	(17) (17)	(23) (23)
(1) (1) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11) (10), (11) (10), (11) 960/LA75, 860/LA85 960/LA75, 860/LA85	(16) (16) (16) LA75 LA75	(17) (17) (17) (23) (24) (24)	(23) (23) (23) (24) (24)
(1) (1) (1)	(10), (11) (10), (11) (10), (11)	(16) (16) LA75, (16)	(18) (18) (18)	(23) (23) (23), (24)
Excalibur 7018, 7018-1, LH-78 MR, (4)		(16)	(17)	(23)
LH-8018-C3 MR, (1), (6), Excalibur 8018-C3 MR, (1), (6)	AXXX10/L61, 880,880M/LAC-Ni2  960,860/LA75 (15)	(29)	(22)	(23), (25)
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1 LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR, (4)		(16) (16) (16)	(17) (17) (17)	(23) (23) (23)
Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR		(16) (16) LA75	(17) (17) (19)	(23) (23) 81Ni1-H
(1)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
(2) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (14) (14)	(16) (16) LA90 LA90	(17) (17) (23) (23)	(23) (23) (24) (24)
(2) (2) (2) Excalibur 9018-M MR	(10), (11) (10), (11) (10), (11) (14)	(16) (16) (16) LA90, MC900	(17) (17) (17)	(23) (23) (23) 91K2-H
LH-8018-C3 MR, C1 MR, Excalibur 8018-C3 MR, C1 MR LH-8018-C3 MR, C1 MR, Excalibur 8018-C3 MR, C1 MR	(10)  (10), 880M/L56	LA75  LA75		(24)  (24)
(1) Excalibur 9018-M MR LH-110M MR	LA90	(16)  LA100, MC1100	(18) 91K2-H	(23)



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A616	Rail-Steel Bars For Concrete Reinforcement (Max 1.410" Dia.) (Discontinued 9/99, replaced with A996)	50 60	80 min 90 min	50 min 60 min
A617	Axle-Steel for Concrete Reinforcement (Max 1.410" Dia.) (Discontinued 9/99, replaced with A996)	40 60	70 min 90 min	40 min 60 min
A618	Low Alloy Structural Tubing	Ia,Ib,II, </= 3/4" Wall Thickness  Ia,Ib,II, > 3/4" Wall Thickness  III	70 min  67 min  65 min	50 min  46 min  50 min
A620	Steel Sheet, Drawing Quality, Special Killed (Discontinued 8/00, replaced with A1008)		40 min	20 min
A633	Normalized High Strength Low Alloy Structural	A	63-83	42 min
		C	70-90 & 65-85	50 min & 46 min
		D	70-90 & 65-85	50 min & 46 min
		E </= 2.5" & >2.5" - 4"	80-100	60 min & 55 min
		E > 4"	75-95	55 min
A656	High Strength, Low Alloy Structural	50 60 70 80	60 min 70 min 80 min 90 min	50 min 60 min 70 min 80 min
A660	Cast Pipe, for High Temperature Service	WCA	60 min	30 min
		WCB	70 min	36 min
		WCC	70 min	40 min
A662	Pressure Vessel, Low & Moderate Temp.	A (CVN Req - 15 ft-lbs @ -75° F) B (CVN Req - 15 ft-lbs @ -50° F) C (CVN Req - 15 ft-lbs @ -50° F)	58-78 65-85 70-90	40 min 40 min 43 min
A668	Carbon & Alloy Steel forgings Minimum Tensiles & Yields Requirements vary with size of forging.	A (Untreated) B (Annealed, or normal, or normal & temp.) C (Annealed, or normal, or normal & temp.) D (Normal, annealed, or normal & temp.) E (Normal&temp, or double normal & temp)	47 min 60 min 66 min 75 min 83 & 85 min	30 min 33 min 37 min 43 & 44 min
		F (Quench&temp,ornormal,quench,&temp.) G (Annealed, or normal,or normal & temp.) H (Normal & temp.) J (Normal&temp, or normal,quech,&temp.) K (Normal,quench, & temp.) L (Normal,quench, & temp.) M (Normal,quench, & temp.) N (Normal,quench, & temp.)	82, 85, & 90 min 80 min 90 min 90 & 95 min 100 & 105 min 110,115, &125 min 135,140 &145 min 160,165 &170 min	48, 50, & 55 min 50 min 58 & 60 min 65 & 70 min 75 & 80 min 85, 95, 105 min 110,115 &120 min 130, 135 &140 min
		Grade designates type of plate used to make pipe. See ASTM Spec. for plate material information.		
		45 50 55 60 65 70 75 80 90	45-55 50-60 55-65 60-72 65-77 70-85 75-90 80 min 90 min	22.5 min 25 min 27.5 min 30 min 32.5 min 35 min 37.5 min 40 min 55 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR		LA75 LA90		(24) 91K2-H
(1) Excalibur 9018-M MR		(16) LA90	(18)	(23) 91K2-H
Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR	(10), (11) (10), (11) (10), (11)	(16) (16) (16)	(18) (18) (18)	(23) (23) (23)
(2)		(16)	(18)	(23)
LH-8018-C3 MR, (1), Excalibur 8018-C3 MR, (1) LH-8018-C3 MR, (1), Excalibur 8018-C3 MR, (1)	(10), 860, 882/L61, 880M/L50 (10), 860, 882/L61, 880M/L51	(16) LA75, (16)	(17) (18)	(23) (23)
LH-8018-C3 MR, (1), Excalibur 8018-C3 MR, (1) LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), 860, 882/L61, 880M/L52 880M/L56, AXXX10/L61, 860/LA-71	LA75, LA90 LA75, LA90	(18)	(23) (24)
LH-8018-C3 MR, Excalibur 8018-C3 MR	880M/L56, AXXX10/L61, 860/LA-71	LA75, LA90		(24)
(1) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (10), 880M/LA-71 (14), 880M, MIL800-H/LA100	(16) (16) LA75, LA90 LA90, MC900, LA100	(18) (18)	(23) (23) (24) 91K2-H
Excalibur 7018, 7018-1, LH-78 MR, (4) Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR	(10), (11) (10), (11) (10), (11)	(16) (16) (16)	(18) (18) (18)	(23) (23) (23)
Excalibur 7018-1 Excalibur 7018-1 Excalibur 7018-1	8500/L-S3 8500/L-S3 8500/L-S3	LA75 LA75 LA75	NR-207 (19) (19)	(24) (24) (24)
(2) (2) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11) (10), (11) (10), (11) (10), (11) (14)	(16) (16) (16) LA75, (16) LA75, LA90, MC900	(17) (17) (17)	(23) (23) (23)
LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR Excalibur 9018-M MR LH-110M MR	(14) (14) (13) (13) (14) (14)	LA75, LA90 LA75, LA90 LA90, MC900 LA90, MC900 LA100, MC1100 LA100, MC1100		(23) (23) 91K2-H 91K2-H
(2) (2) (2) (2) (1) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (10), (11) (10), (11) (10), (11) (10), (11) (10), (11)	(16) (16) (16) (16) (16) (16) (16)	(17) (17) (17) (17) (17) (17) (17)	(23) (23) (23) (23) (23) (23) (23)



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A678	Quenched & Tempered Structural Plate	A B C [ $< 3/4"$ , $3/4" - 1-1/2"$ , $1-1/2" - 2"$ ] D	70-90 80-100 85-105, 90-110, 95-115 90-110	50 min 60 min 65, 70, & 75 min 75 min
A690	H-Piles & Sheet Piling		70 min	50 min
A691	Carbon and Alloy Steel Pipe, (> 16" Dia.)	Grade designates type of plate used to make pipe. See ASTM Spec. for plate material information.		
A692	Seamless L.A. Steel Tubes, 1/2% Mo. (5" Max. Dia.)	64-84	42 min	SA-85
A694	Carbon & Alloy Steel forgings	F42	60 min	42 min
		F46	60 min	46 min
		F48	62 min	48 min
		F50	64 min	50 min
		F52	66 min	52 min
		F56	68 min	56 min
		F60	75 min	60 min
		F65	77 min	65 min
		F70	82 min	70 min
A695	Bars, for Fluid Power	35 Type A, B, C, & D 40 Type A, B, C, & D 45 Type A, C, & D 50 Type A, C, & D	60 min 70 min 80 min 90 min	35 min 40 min 45 min 50 min
A696	Carbon Steel Bars - Pressure Piping Components	B	60 min	35 min
		C	70 min	40 min
A706	Low Alloy Bars for Concrete Reinforcement		80 min	60 min, 78 max
A707	Carbon & Alloy Steel Flanges for Low Temp. Service Impact Test Temperatures - L1 @ -20°F	L1, Class 1 & 2	60 & 66 min	42 & 52 min
		L2, Class 1, 2, & 3	60, 66, & 75 min	42, 52, & 60 min
	L2 & L3 @ -50°F L4, L5, & L6 @ -80°F L7 & L8 @ -100°F	L3, Class 1, 2, & 3	60, 66, & 75 min	42, 52, & 60 min
		L4, Class 1, 2, & 3	60, 66, & 75 min	42, 52, 60, & 75 min
		L5, Class 1, 2, 3, & 4	60, 66, 75, & 90 min	42, 52, 60, & 75 min
		L6, Class 1, 2, 3, & 4	60, 66, 75, & 90 min	42, 52, & 60 min
		L7, Class 1, & 2	60 & 66 min	42 & 52 min
		L8, Class 1, 2, 3, & 4	60, 66, 75, & 90 min	42, 52, 60, & 75 min
A709	Structural Steel For Bridges. For bridge fabrication, AASHTO/AWS D1.5 is often applicable. The filler metals listed for A709 include those options that meet both the strength requirements for the application, as well as meeting the requirements of D1.5-2002.	36 (Similar to A36)	58 min & 58-80	36 min
		50 (Similar to A572, Grade 50)	65 min	50 min
		50S (Similar to A992)	65 min	50-65
		50W, Type A, B, & C (Similar to A588)	70 min	50 min
		70W (Similar to A852)	90-110	70 min
		HPS 50W	70 min	50 min
		HPS 70W	90-110	70 min
		100, 100W, $\leq 2-1/2"$ (Similar to A514)	110-130	100 min
		100, 100W, $2-1/2" to 4"$ (Similar to A514)	100-130	90 min
A710	Low-C Age-Hardening Gr. A (.85% Ni, .75% Cr, +Cu, Mo, Cb), Gr B (1.25% Ni + Cu & Cb), Gr. C (.85% Ni, + Mo, Cu, & Cb) Class 1- As-rolled & Precipitation Heat Treated, Class 2- Normalized & Precipitation Heat Treated, Class 3- Quenched & Precipitation Heat Treated,	A, Class 1 {CVN Req't 20 ft-lb @ -50°F}	90 min	80 & 85 min
		A, Class 2 {CVN Req't 50 ft-lb @ -50°F}	60, 65, & 72 min	50, 55, 60, & 65 min
		A, Class 3 {CVN Req't 50 ft-lb @ -80°F}	70, 75, & 85 min	60, 65, & 75 min
		B (As-Rolled & Precipitation Heat Treated)	88 & 90 min	75, 80, 82, 85 min
		C, Class 1	100 min	90 min
		C, Class 3 {CVN Req't 50 ft-lb @ -80°F}	90 & 95 min	80 & 85 min
A714	Low Alloy Pipe Type F- Furnace Butt Welded Type E- Electric-Resistance Welded Type S- Seamless Grades I, II, & III- Class 2 Pipe <b>(A714 continued on next page)</b>	I	70 min	50 min
		II	70 min	50 min
		III	65 min	50 min
		IV (.2-.5% Ni, 1% Cr)	58 min	36 min
		V, Type F & Type E, S (2% Ni)	55 min & 65 min	40 min & 46 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
LH-8018-C3 MR, (1) LH-8018-C3 MR LH-110M LH-110M See A588	(10), (11) (10), (11) 8500/LA85 8500/LA85 See A588	(16) LA75, LA90 LA100, MC1100 LA100, MC1100 See A588	(18)	(23) (24) 91K2-H 91K2-H See A588
		LA90		
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR LH-8018-C3 MR, LH-D80, LH-D90 LH-8018-C3 MR, LH-D80, LH-D90 Excalibur 9018-M MR	(10), (11) (10), (11) (10), (11) (10), (11) (10), (11) (10), (11) (10), (11) (10), (11) 880M, 882, 960/LA92, 880M/LA90	(16) (16) (16) (16) (16) (16) (16) (16) LA90	(18) (18) (18) (18) (18) (18) (18) (18) (23) (23) (23) (23) (23) (23) (23) 81K2-H	
(2) (3) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (10), (11) (13)	(16) (16) LA75, LA90 LA90, MC900	(17) (17)	(23) (23) (24) 91K2-H
Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR		(16) (16)	(18) (18)	(23) (23)
LH-8018-C3 MR		LA75, LA90		(24)
Excalibur 7018-1 Excalibur 7018-1 Excalibur 7018-1	(10), (11) 960, 860, 880M/LA75 960, 860, 880M/LA75	(16) LA75 LA75	(18) NR-207 NR-207	(23) 81K2-H 81K2-H
LH-8018-C1 MR, Excalibur 8018-C1 MR LH-8018-C1 MR, Excalibur 8018-C1 MR LH-8018-C1 MR, Excalibur 8018-C1 MR	880M/LA75 880M/LA100 880M/LA100 880M/LAC-Ni2	LA75 LA75 LA75	NR-207 NR-207 NR-207	91K2-H 91K2-H 91K2-H
(1) (1) (1) (1), (6) Excalibur 9018-M MR (1), (6) Excalibur 9018-M MR LH-110M MR LH-110M MR	(10), (11) (10), (11) (10), (11) (15) MIL800HPNi/LA85, (31) (15) MIL800HPNi/LA85, (31) (12) (12)	(16)	(18) (18) (17) (22)	(23) (23) (23) (25) 91K2-H (22) (25)
Excalibur 9018-M MR Excalibur 7018-1 LH-8018-C1 MR, Excalibur 8018-C1 MR Excalibur 9018-M MR LH-110M MR	880M/LA100 880M/LA75 880M/LA100 (14) (13) (12)	LA100 LA75 LA90 LA100, MC1100 LA100	NR-207	91K2-H 91K2-H
Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C1 MR, Excalibur 8018-C3 MR	(10), (11) (10), (11) (10), (11) 860/LA75 880, 880M/LAC-Ni2	(16) (16) (16) LA75	(18) (18) (18) NR-203 Ni1%	(23) (23) (23) 81Ni1-H



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A714 <i>(contd)</i>	Grades IV, V, VI, VII, & VIII- Class 4 Pipe (Class 4- 4 times Corrosion Resistance of Carbon Steel)	VI, Type E&S (.75% Ni,.33% max Cr,.15% Mo) VII, Type E&S (.24 - 1.3% Cr,.68% Ni) VIII, Type E & S (.5% Ni)	65 min 65 min 70 min	46 min 45 min 50 min
A715	High Strength, Low-Alloy Sheet & Strip (Discontinued 8/00, replaced with A1008 & A1011)	50 60 70 80	60 min 70 min 80 min 90 min	50 min 60 min 70 min 80 min
A724	Pressure Vessel Plates Quenched & Tempered C-Mn-Si Steel	A B C	90-110 95-115 90-110	70 min 75 min 70 min
A727	Notch-Tough Carbon Steel Forgings		60-85	36 min
A732	Castings, for High Strength at Elevated Temperatures	1A, 2A, 3A 2Q, 5N 4A, 6N (.4%Mo) 3Q, 13Q 11Q (1.75% Ni), 4Q	60, 65, 75 min 85 min 90 min 100 & 105 min 120 & 125 min	40, 45, & 48 min 60 & 55 min 50 & 60 min 90 & 85 min 85 & 90 min
A734	Pressure Vessel Plates, High Strength, Low Alloy, Quenched & Tempered	Type A (1%Ni, 1%Cr,.35%Mo, for use @-80° F) Type B (for use @ -20° F)	77-97 77-97	65 min 65 min
A735	Pressure Vessel Plates Low C-Mn-(.4%) Mo-Cb for Moderate & Lower Temperature Service	Class 1 Class 2 Class 3 Class 4	80-100 85-105 90-110 95-115	65 min 70 min 75 min 80 min
A736	Pressure Vessel Plates Low-C Age-Hardening Gr A (.85% Ni,.75% Cr, +Cu, Mo, Cb) Gr C (.85% Ni,+Cu, Mo, Cb)	A, Class 1 A, Class 2 A, Class 3 C, Class 1 C, Class 3	90-110 60-80 to 72-92 70-90 to 85-105 100 -120 90-110 to 95-115	80 min 50 min to 65 min 60 min to 75 min 90 min 80 min to 85 min
A737	Pressure Vessel Plates, High-Strength, Low-Alloy	B C	70-90 80-100	50 min 60 min
A738	Pressure Vessel, Heat Treated, C-Mn-Si, for Moderate & Low Temperature Service	A (</= 2.5" Norm or Q & T, > 2.5" Q & T) B (All Thicknesses Quenched & Tempered) C (All Thicknesses Quenched & Tempered)	75-95 85-102 70-90 to 80-100	45 min 60 min 46, 55, & 60 min
A739	Steel Bars, for Elevated Temperature or Pressure Contain Parts	B 11 (1.25% Cr, .5% Mo) B 22 (2.25% Cr, 1% Mo)	70-95 75-95	45 min 45 min
A757	Steel Castings, for Pressure Containing, for Low Temperature Service Q's-Quenched & Tempered N's- Normalized & Tempered,	A1Q, A2Q (CVN's @ -50°F) B2N, B2Q (2.5% Ni), (CVN's @ -100°F) C1Q (1.75% Ni,.2% Mo), (CVN's @ -50°F) D1N1, D1Q1 (2.5% Cr,1% Mo) D1N2, D1Q2 (2.5% Cr,1% Mo)	65 & 70 min 70 min 75 min 85 & 115 min 95 & 125 min	35 & 40 min 40 min 55 min 55 min 75 min
A758	Pipe Fittings with Improved Notch Tough.	60 70	60-85 70-95	35 min 38 min
A765	Pressure Vessel Forgings with Mandatory CVN Req'ts CVN Test Temperature - Grades I & IV @ -20° F, Grade II @ -50° F, Grade III @ -150° F	I II III (3.5% Ni) IV	60-85 70-95 70-95 80-105	30 min 36 min 37.5 min 50 min
A769	Carbon & High-Strength Electric Resistance Welded Steel Structural Shapes W indicates Steel Grades having Atmospheric Corrosion Resistance Approx. 2 times that of Carbon Structural Steel with Copper. Class 1 - General Structural use for Static Loads Class 2 - Structural use where Fatigue Loading Occurs	36 40 45 45W 50 50W 60 80	53 min 55 min 60 min 65 min 65 min 70 min 75 min 90 min	36 min 40 min 45 min 45 min 50 min 50 min 60 min 80 min
A782	Pressure Vessel Plates, Quenched & Tempered Mn-Cr-Mo-Si-Zr	Class 1 (.75% Cr, .4% Mo) Class 2 (.75% Cr, .4% Mo) Class 3 (.75% Cr, .4% Mo)	97-119 107-129 115-136	80 min 90 min 100 min
A808	High-Strength, Low-Alloy, Structural C-Mn-Cb-V, CVN's @ -50° F		60, 65, & 65 min	42, 46, & 50 min
A812	High-Strength, Low-Alloy Sheet, Pressure Vessels Specification was discontinued 1997	65 80	85-110 100-125	65 min 80 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR	860/LA75 860/LA75 860/LA75	LA75 LA75 LA75	NR-203 Ni1% NR-203 Ni1% NR-203 Ni1%	81Ni1-H 81Ni1-H 81Ni1-H
(2) (3) LH-8018-C3, Excalibur 8018-C3		(16) (16) LA75 LA90, MC900	(17) (17)	(23) (23) (24) 91K2-H
LH-110M MR LH-110M MR LH-110M MR	8500/LA85 8500/LA85 8500/LA85	LA100, MC1100 LA100, MC1100 LA100, MC1100		91K2-H 91K2-H 91K2-H
Excalibur 7018, 7018-1, LH-78 MR (1) Excalibur 9018-M MR LH-110M MR	(10), (11) (10), (11) (13) (14) (12)	(16) (16) LA75 LA90, LA100 LA100, MC1100	(18)	(23) (23) (24) 91K2-H
LH-8018-C1 MR, Excalibur 8018-C1 MR Excalibur 9018-M MR	8500, 880M/LA85 8500/L-S3	LA100 LA75		81K2-H 81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR Excalibur 9018-M MR LH-110M MR	(34) 880M/LA90 880M/LA90 MIL800-H, 880M/LA100	LA75 LA90 LA90, MC900 LA100, MC900		81K2-H 81K2-H 91K2-H 91K2-H
Excalibur 7018-1 LH-8018-C1 MR, Excalibur 8018-C1 MR LH-110M MR LH-110M MR	(14) (10), (11) (14) (12) (12)	LA100 (16) LA75 LA100, MC1100 LA100, MC1100	(18)	91K2-H (23) (24)
(1) LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11) (10), (13)	(16) L-75, LA90	(18)	(23) (24)
LH-8018-C3 MR, Excalibur 8018-C3 MR	860, 880M, 882/LA-71 (14) (14)	LA75 LA75, LA100 LA75, LA100		(24) 91K2-H, (24) 91K2-H
LH-90 MR, Jet-LH 8018-B2 MR Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA92, (26) MIL800-H, 880M, 882/LA93			
Excalibur 7018-1, LH-75 MR LH-8018-C1 MR, Excalibur 8018-C1 MR LH-8018-C1 MR, Excalibur 8018-C1 MR LH-110M MR	880M/LA75 880M/LAC-Ni2 880M/LA75 (12)	LA75 LA75 LA100, MC1100	(19)	81K2-H 81K2-H
Excalibur 7018, 7018-1, LH-78 MR Excalibur 7018, 7018-1, LH-78 MR	(10), (11) (10), (11)	(16) (16)	(18) (18)	(23) (23)
(1) Excalibur 7018-1,	(10), (11) 880M/L56	(16) LA75	(18) (19)	(23) 81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	(14)	LA75		(24)
(2) (2) (2) (3), (6) (3) (3), (6) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (10), (11) (10), (11), (15) (10), (11) (10), (11), (15) (14) (13)	(16) (16) (16) (16), LA75 (16) (16), LA75 LA75 LA100	(17) (17) (17) (17) (17) (17) (19) 91K2-H	(23) (23) (23) (23), (25) (23) (23), (25) (24)
LH-110M MR	(12) (12)	LA100 MC1100	91K2-H	
Excalibur 7018-1	8500/L-S3	LA75	(19)	(24)
Excalibur 9018-M MR LH-110M MR		LA75 LA100, MC1100		81K2-H



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A822	Steel Tubing, Hydraulic Service, 1/8-3 Dia.		45 min	25 min
A832	Pressure Vessel, Cr-Mo-V-Ti-B	Grade 21V (3% Cr, 1% Mo, .25% V-Ti-B)	85-110	60 min
		Grade 22V (2.25% Cr, 1% Mo, .25% V)	85-110	60 min
A841	Pressure Vessel Plates, TMCP	Class 1, up to and including 2.5" & > 2.5" Class 2, up to and including 2.5" & > 2.5"	70-90 & 65-85 80-100 & 75-95	50 min & 45 min 60 min & 55 min
A847	Low Alloy Tubing with Improved Atmospheric Corrosion		70 min	50 min
A850	Steel Bars, C-Mn	Class 1 Class 2	70-99 70-99	50 min 50 min
A852	Quenched & Tempered Low Alloy Structural Plate		90-110	70 min
A858	Heat Treated Fittings for Low-Temp. & Corrosive Service, Max .60% Ni %, .30% Cr, .35% Cu	CVN Req- 20 ft-lbs @ -50° F	70-95	36 min
A859	Steel forgings, Age Harden Ni-Cu-Cr-Mo-Cb	Class 1 Class 2	65-85 75-95	55 min 65 min
A860	High-Strength Fittings CVN Req't - 30 ft-lbs @ -50° F Max. Ni 1.0%, Stress Relieved 1 hour @ 1150° F	WPHY 42	60-85	42 min
		WPHY 46	63-88	46 min
		WPHY 52	66-91	52 min
		WPHY 60	75-100	60 min
		WPHY 65	77-102	65 min
		WPHY 70	80-105	70 min
A871	High-Strength, Low-Alloy, Structural, with Atmospheric Corrosion Resistance	60 65	75 min 80 min	60 min 65 min
A873	Steel Sheet Pressure Vessels, 2.25% Cr-1% Mo for use @ elevated temperatures (Discontinued in 1997)	Class 1	60-85	30 min
		Class 2	75-100	45 min
		Class 3	85-110	60 min
		Class 4	95-120	75 min
		Class 5	130-160	100 min
A907	Sheet & Strip, Hot-Rolled, Structural Quality (Discontinued 6/01, replaced with A1018)	30, 33, 36, & 40	49,52,53, &55 min	30,33,36, &40 min
A913	High-Strength Low Alloy Shapes of Structural Quality, Produced by Quenching & Self-Tempering Process	50	65 min	50 min
		60	75 min	60 min
		65	80 min	65 min
		70	90 min	70 min
A935	Steel, Sheet & Strip, High Strength Low - Alloy Columbium or Vanadium or Both (Discontinued 6/01, replaced with A1018)	45	60 min	45 min
		50, 55, & 60	65 & 70 min	50 & 55 min
		65	80 min	65 min
		70	85 min	70 min
A936	High Strength, Low-Alloy Sheet & Strip, Heavy Thickness Coils (Discontinued 6/01, replaced with A1018)	50	60 min	50 min
		60	70 min	60 min
		70	80 min	70 min
		80	90 min	80 min
A945	High Strength, Low - Alloy Structural Plate w/Low Carbon & Restricted Sulfur for Improved Weldability	50	70-90	50 min
		65	78-100	65min
A984	Steel Line Pipe, black, Plain-End, Electric-Resistance-Welded	35	60 min	35-70
		45	65 min	45-72
		55	70 min	55-80
		65	75 min	65-85
		80	90 min	80-97
A992	Steel for Structural Shapes for use in Building Framing		65 min	50-65
A996	Rail-Steel & Axle-Steel for Concrete Reinforcement	40	70 min	40 min
		50	80 min	50 min
		60	90 min	60 min

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
(2), (4)		(16)		
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
Jet-LH 9018-B3 MR	MIL800-H, 880M, 882/LA93			
(1) LH-8018-C3, Excalibur 8018-C3	(10), (11) 860, 960/LA75	(16) LA75	(18)	(23) 81Ni1-H
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	(10), (11)	(16)	(18)	(23)
(1) (1)	(10) (10)	(16) (16)	(18) (18)	(23) (23)
Excalibur 9018-M MR	MIL800-HPNi/LA85, (31)	MC1100		91K2-H
Excalibur 7018, 7018-1, LH-78, LH-8018-C3 MR, Excalibur 8018-C3 MR	880M/L56	LA75	NR-207	81K2-H
LH-8018-C1 MR, Excalibur 8018-C1 MR LH-8018-C1 MR, Excalibur 8018-C1 MR	880M/LA75 880M/LA75	LA75 LA75		
Excalibur 7018-1 Excalibur 7018-1 Excalibur 7018-1	8500/LS3 8500/LS3 8500/LS3 8500/LA85 8500/LA85			
LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR	860, 960/LA75 860, 960/LA75	LA75 LA75		81Ni1-H 81Ni1-H
Jet-LH 9018-B3L Jet-LH 9018-B3L Jet-LH 9018-B3L	MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA93 MIL800-H, 880M, 882/LA93			
(2)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	761/L61, 860, 960/L50 960/LA75 960/LA75 880M/LA100	LA75 LA75 LA75	(18) NR-311 Ni	(23) (24) (24) (24)
(2) (1) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR	(10), (11) (10), (11) (14) (14)	(16) (16) LA90 LA90	(17) (17)	(23) (23) (24) (24)
(2) (3) LH-8018-C3 MR, Excalibur 8018-C3 MR		(16) (16) LA75 LA90, MC900	(17) (17)	(23) (23) (24) 91K2-H
Excalibur 7018-1 LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85 8500/L-S3, LA85	LA75 LA75	NR-203MP	(24) 81K2-H
(2), (4) Pipelin 6P+, Pipelin 8P+, FW 5P+, SA HYP+, SA 70+, SA 80 SA 70+, SA 80, SA HYP+, LH-D80, LH-D90, Pipelin 8P+ SA 70+, SA 80, LH-D80, LH-D90, Pipelin 8P+ SA 90 (28), LH-D90,	860/L60, L61 860/L60, L61 860/L60, L61 860/L60, L61 880M/LA90	(16) (16) L56 L56 LA90	(21) (21) (21) (21)	(23) (23) (24) (24) 91K2-H
(1)	(10), (11)	(16)	(17)	(23)
(1) LH-8018-C3 MR, Excalibur 8018-C3 MR Excalibur 9018-M MR		(16) LA75 LA90	(18)	(23) (24) 91K2-H



## FILLER METAL SELECTOR GUIDE

ASTM NO.	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
A1008	Steel, Sheet, Cold-Rolled, Structural, High Strength Low-Alloy. High-Strength Low-Alloy with Improved Formability.	CS,(Types A, B, & C), DS, { (Types A & B), DDS, EDDS } SS, Grades 25, 30, 33, & 40 SS, Grade 80 HSLAS, Grade 45 Class 1 & 2 HSLAS, Grade 50 Class 1 & 2 HSLAS, Grade 55 Class 1 & 2 HSLAS, Grade 60 Class 1 & 2 HSLAS, Grade 65 Class 1 & 2 HSLAS, Grade 70 Class 1 & 2 HSLAS-F Grade 50 HSLAS-F Grade 60 HSLAS-F Grade 70 HSLAS-F Grade 80	— 42,45,48, &52 min 82 min 60 & 55 65 & 60 70 & 65 min 75 & 70 min 80 & 75 min 85 & 80 60 min 70 min 70 min 80 min 90 min	20-40, 22-35, 17-29,15-25 25,30,33, &40 min 80 min 45 min 50 & 55 50 & 55 60 & 65 60 & 65 70 min 50 min 60 min 70 min 80 min
A1011	Steel, Sheet, Hot-Rolled, Structural, High Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability.	CS,(Types A, B, & C), DS,types (A & B) SS, Grades 25, 30, 33, & 40 SS, Grade 80 HSLAS, Grade 45 Class 1 & 2 HSLAS, Grade 50 Class 1 & 2 HSLAS, Grade 55 Class 1 & 2 HSLAS, Grade 60 Class 1 & 2 HSLAS, Grade 65 Class 1 & 2 HSLAS, Grade 70 Class 1 & 2 HSLAS-F Grade 50 HSLAS-F Grade 60 HSLAS-F Grade 70 HSLAS-F Grade 80	— 42,45,48, &52 min 82 min 60 & 55 min 65 & 60 min 70 & 65 min 75 & 70 min 80 & 75 min 85 & 80 min 60 min 70 min 80 min 90 min	20-40, 22-35, 17-29,15-25 25,30,33, &40 min 80 min 45 min 50 & 55 min 50 & 55 min 60 & 65 min 60 & 65 min 70 min 50 min 60 min 70 min 80 min
A1018	Steel, Sheet, Hot-Rolled, Structural, High Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability.	SS, Grades 25, 30, 33, & 40 SS, Grade 80 HSLAS, Grade 45 Class 1 & 2 HSLAS, Grade 50 Class 1 & 2 HSLAS, Grade 55 Class 1 & 2 HSLAS, Grade 60 Class 1 & 2 HSLAS, Grade 65 Class 1 & 2 HSLAS, Grade 70 Class 1 & 2  HSLAS-F Grade 50 HSLAS-F Grade 60 HSLAS-F Grade 70 HSLAS-F Grade 80	42,45,48, &52 min 82 min 60 & 55 65 & 60 min 70 & 65 min 75 & 70 min 80 & 75 min 85 & 80 min  60 min 70 min 80 min 90 min	25,30,33, &40 min 80 min 45 min 50 & 55 50 & 55 60 & 65 60 & 65 70 min  50 min 60 min 70 min 80 min

\*\* For Gas Shielded processes (GMAW & FCAW-G), the type of gas shielding used will affect the electrode operability characteristics and mechanical properties. All suggestions listed in this guide are based on the resultant mechanical properties when the electrode is used with the shielding gas required for AWS classification. Changes in shielding gas may make the suggestions inappropriate, or create new options. Selecting the correct shielding gas is beyond the scope of this document.

**FILLER METAL SELECTOR GUIDE**

SMAW	SAW	GMAW**	FCAW-S	FCAW-G**
(2)	(10), (11)	(16)	(17)	(23)
(2) Excalibur 9018-M MR	(10), (11) 880M, 8500/LA90	(16) LA90	(17)	(23) 91K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
Excalibur 9018-M MR	880M, 8500/LA90	LA90		91K2-H
(2)	(10), (11)	(16)	(17)	(23)
(2) Excalibur 9018-M MR	(10), (11) 880M, 8500/LA90	(16) LA90	(17)	(23) 91K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500/L-S3, LA85	LA75		81K2-H
Excalibur 9018-M MR	880M, 8500/LA90	LA90		91K2-H
(2)	(10), (11)	(16)	(17)	(23)
Excalibur 9018-M MR	880M, 8500/LA90	LA90		91K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500, 8500-H2/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500, 8500-H2/L-S3, LA85	LA75		81K2-H
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500, 8500-H2/L-S3, LA85	LA75		81K2-H
(2)	(10), (11)	(16)	(17)	(23)
(1)	(10), (11)	(16)	(17)	(23)
LH-8018-C3 MR, Excalibur 8018-C3 MR	8500, 8500-H2/L-S3, LA85	LA75		81K2-H
Excalibur 9018-M MR	880M, 8500/LA90	LA90		91K2-H



## **AMERICAN PETROLEUM INSTITUTE FILLER METAL SELECTOR GUIDE**

API SPEC	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
2H	C-Mn Steel plate for Offshore Platform	42 (CVN Requirement 25 ft-lbs @ -40 F)	62-82	42 min
		50,</= 2.5(CVN Requirement 30ft-lbs@-40F)	70-90	50 min
		50, > 2.5(CVN Requirement 30 ft-lbs @-40F)	70-90	47 min
2W	Steel Plates for Offshore Structures, Produced by Thermo-Mechanical Control Processing (TMCP)	42 (CVN Requirement 25 ft-lbs @ -40 F)	62 min	42-67
		50 (CVN Requirement 30 ft-lbs @ -40F)	65 min	50-75
		50T (CVN Requirement 30 ft-lbs @ -40F)	70 min	50-80
		60 (CVN Requirement 35 ft-lbs @ -40F)	75 min	60-90
2Y	Steel Plates, Quenched & Tempered, for Offshore Structures	42 (CVN Requirement 25 ft-lbs @ -40 F)	62 min	42-67
		50 (CVN Requirement 30 ft-lbs @ -40F)	65 min	50-75
		50T (CVN Requirement 30 ft-lbs @ -40F)	70 min	50-80
		60 (CVN Requirement 35 ft-lbs @ -40F)	75 min	60-90
5L	Welded Steel Line Pipe	Product Specification Level (PSL) 1 A25	45 min	25 min
		A	48 min	30 min

(5L continued on next page)

Product Specification Levels (PSL) were added to the specification January 2000. PSL2 has mandatory requirements for carbon equivalent, notch toughness, maximum yield strength, and maximum tensile strength.

**AMERICAN PETROLEUM INSTITUTE  
FILLER METAL SELECTOR GUIDE**

SMAW	SAW***		GMAW**	FCAW-S	FCAW-G**
	Double-Ending	Longitudinal & Spiral Seam*			
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
LH-8018-C3 MR	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75		(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
Excalibur 7018-1	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75	(19)	(24)
LH-8018-C3 MR	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	880M/L50, L-S3, LA85, 960/L50, L61, LA85, 882, 8500, 860/L50, L-S3, L61, LA85	LA75		(24)
(2), (4)	860/L60, L61	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
(2), (4)	860/L60, L61	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	



**AMERICAN PETROLEUM INSTITUTE  
FILLER METAL SELECTOR GUIDE**

API SPEC	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
5L <i>(contd)</i>	Welded Steel Line Pipe	B	60 min	35 min
		X42	60 min	42 min
		X46	63 min	46 min
		X52	66 min	52 min
		X56	71 min	56 min
		X60	75 min	60 min
		X65	77 min	65 min
		X70	82 min	70 min
	<i>Product Specification Level (PSL) 2</i>	B	60-110	33-65
		X42	60-110	42-72
		X46	63-110	46-76
		X52	66-110	52-77
		X56	71-110	56-79
<i>(5L continued on next page)</i>				

Product Specification Levels (PSL) were added to the specification January 2000. PSL2 has mandatory requirements for carbon equivalent, notch toughness, maximum yield strength, and maximum tensile strength.

**AMERICAN PETROLEUM INSTITUTE  
FILLER METAL SELECTOR GUIDE**

SMAW	SAW***		GMAW**	FCAW-S	FCAW-G**
	Double-Ending	Longitudinal & Spiral Seam*			
(2), (4)	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
(2), (4)	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
(2), (4)	860/L60, L61	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5, FW 5P+, SA HYP+, SA 70+, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5P+,SAHYP+,SA 70+,SA 80, 16P, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5P+,SAHYP+,SA 70+,SA 80, 16P,18P, LH-D80, LH-D90, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5P+,SAHYP+,SA 70+,SA 80, 16P,18P, LH-D80, LH-D90, Pipeliner 6P+, Pipeliner 8P+	860/L50,L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L56	NR-207,-H	
SA 70+, SA 80, 18P, LH-D80, LH-D90, Pipeliner 8P+	882/LA-71, LA75	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90		NR-207,-H	
(2), (4)	860/L60, L61	995/L61, L70, LA81, LA90 780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
(2), (4)	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
(2), (4)	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5, FW 5P+, SA HYP+, SA 70+, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5P+,SAHYP+,SA 70+,SA 80, 16P, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761,P223/L61,L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	



**AMERICAN PETROLEUM INSTITUTE  
FILLER METAL SELECTOR GUIDE**

API SPEC	DESCRIPTION	GRADES	STRENGTH REQUIREMENTS	
			TENSILE (ksi)	YIELD (ksi)
5L <i>(contd)</i>	Welded Steel Line Pipe	X60	75-110	60-82
		X65	77-110	65-87
		X70	82-110	70-90
		X80	90-120	80 min

Product Specification Levels (PSL) were added to the specification January 2000. PSL2 has mandatory requirements for carbon equivalent, notch toughness, maximum yield strength, and maximum tensile strength.

\* Welding on 2H, 2Y, and 2W grades is assumed to be multipass and longitudinal only. Welding on 5L grades is assumed to be single pass.

\*\* For Gas-Shielded processes (GMAW & FCAW-G), the type of gas shielding used will affect the electrode operability characteristics and mechanical properties. All suggestions listed in this guide are based on the resultant mechanical properties when the electrode is used with the shielding gas required for AWS classification. Changes in shielding gas may make the suggestions inappropriate, or create new options. Selecting the correct shielding gas is beyond the scope of this document.

\*\*\* SAW recommendations are starting points only. Because of the varying requirements and the high dilution rates involved with pipe welding, all combinations should be tested on the pipe to be used to assure that all requirements are met.

**AMERICAN PETROLEUM INSTITUTE  
FILLER METAL SELECTOR GUIDE**

SMAW	SAW***		GMAW**	FCAW-S	FCAW-G**
	Double-Ending	Longitudinal & Spiral Seam*			
FW 5P+, SAHYP+, SA 70+, SA 80, 16P, 18P, Pipeliner Lincoln LH-D80, Pipeliner Lincoln LH-D90, Pipeliner 6P+, Pipeliner 8P+	860/L60, L61	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L50, L56	NR-207,-H	
FW 5P+, SAHYP+, SA 70+, SA 80, 16P, 18P, Pipeliner Lincoln LH-D80, Pipeliner Lincoln LH-D90, Pipeliner 6P+, Pipeliner 8P+	860/L50, L61	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90	L56	NR-207,-H	
SA 70+, SA 80, 18P, LH-D80, Pipeliner Lincoln LH-D90, Pipeliner 8P+	882/LA-71, LA75	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90		NR-207,-H	
SA70+, SA80 (Both Root Only), SA90(28), 18P, LH-D90,	MIL800-H, 880M/LA100	780/L61, 761, P223/L61, L70 997/L61, L70, LA81 995N/L70, LA81, LA90 995/L61, L70, LA81, LA90			

